
LIST OF FIGURES

Figure No	Figure Captions	Page No
Fig. 1.1	Sources of electricity in India by installed capacity as of 2016	1
Fig. 1.2	Comparison of life-cycle emissions	2
Fig. 1.3	Three stage Indian nuclear power programme	3
Fig. 1.4	Schematic flow diagram of PFBR showing the major components.	4
Fig. 1.5	FBR Fuel assembly	6
Fig. 1.6a	Schematic arrangement of steam generator	11
Fig. 1.6b	Schematic arrangement of steam generator bottom tube sheet	12
Fig. 1.7	Volumetric swelling vs. neutron fluence in austenitic and ferritic steels	16
Fig. 1.8	Comparison creep ruptures strength of several materials for 10^5 h	18
Fig. 1.9	Schematic pseudo-equilibrium Fe (with 0.1%C)-Cr phase diagram. The dashed line indicates the phase fields for steel for 9% Cr	19
Fig. 1.10	Continuous cooling transformation diagram for 9Cr-1Mo steel	20
Fig. 1.11	LCF during start-up and shutdown of steam generator structural components	22
Fig. 1.12	(a) Types of serrations (b) Schematic illustrations of various manifestations of dynamic strain ageing under monotonic loading	24
Fig. 1.13	The three stages of the mechanical behavior with respect to the temperature in modified 9Cr-1Mo steel	27
Fig. 1.14	(a) Variation of prior austenitic grain size after 5 min soaking at different temperatures (b) Variation of the inter-barrier spacing of the steel soaking at various	28

	temperatures	
Fig. 1.15	Tensile curves of the steel soaked at different temperatures, tensile tested at 300 °C	29
Fig. 1.16	Schematic depicting the mechanism of DSA through pipe diffusion	31
Fig. 1.17	Growth and coarsening of precipitate particles of Grade 91 ferritic/martensitic steel	32
Fig. 1.18	Comparison of LCF life of modified 9Cr–1Mo steel in air and sodium environments at 550 °C	36
Fig. 1.19	Fatigue lives of T91 steel in an oxygen controlled LBE and in vacuum at 350 °C	38
Fig. 1.20	Influence of temperature on (a) fatigue life and (b) half–life stress of modified 9Cr–1Mo and 1.4W–0.06Ta RAFM steels	41
Fig. 1.21	Comparison between experimental and simulated cyclic softening for (a) $\Delta\varepsilon_t = 1\%$ and (b) $\Delta\varepsilon_t = 0.4\%$	45
Fig. 2.1	Flow chart of the processing and heat treatment	48
Fig. 2.2	Geometry of the cylindrical tensile specimen with dimensions in mm	49
Fig. 2.3	Samples fabricated from different orientations of blanks from the plate	51
Fig. 2.4	Schematic of the cylindrical LCF specimen with dimensions in mm	52
Fig. 2.5	Schematic of the reversed triangular waveform	53
Fig. 2.6	Inverted torsional pendulum for internal friction measurement	54
Fig. 3.1	Microstructure of the modified 9Cr-1Mo steel in normalized and tempered condition: (a) optical micrograph, (b) SEM micrograph, (c) TEM micrographs showing laths (L) inside the prior austenite grain boundary (PAGb), carbides along the PAGb, and lath boundary and within the laths, (d) high dislocation density within the laths, (e) diffraction pattern of matrix, and (f) diffraction pattern of the $M_{23}C_6$ carbide encircled in (c)	57

Fig. 3.2	Engineering stress–strain curves corresponding to different temperatures at different strain rates: (a) 10^{-3} s^{-1} , (b) 10^{-4} s^{-1} , (c) magnified view of the portion encircled in rectangular box in the fig. (b), & (d) 10^{-5} s^{-1}	59
Fig. 3.3	Variation of strength with temperature at different strain rates of 10^{-3} , 10^{-4} & 10^{-5} s^{-1} : (a) yield strength (b) ultimate tensile strength	60
Fig. 3.4	Variation of plastic strain with test temperature: (a) plastic strain to fracture (e_{pf}) at different strain rates, (b) different components of plastic strain (e_{pf} , e_{pu} & e_{pn}) at strain rate of 10^{-4} s^{-1}	61
Fig. 3.5	Variation of strain hardening exponent (n) with temperature for the modified 9Cr-1Mo steel at different strain rates 10^{-3} s^{-1} , 10^{-4} s^{-1} and 10^{-5} s^{-1}	62
Fig. 3.6	Variation of strain rate sensitivity with temperature based on: (a) yield strength, (b) tensile strength	63
Fig. 3.7	Variation of $\ln \dot{\epsilon}$ with reciprocal test temperature	64
Fig. 3.8	Variation of Vickers microhardness of tensile specimens tested at different temperatures and strain rates	65
Fig. 3.9	Dislocation substructure below the region of DSA, at RT, at strain rate 10^{-4} s^{-1}	66
Fig. 3.10	Dislocation substructure below the region of DSA, at 200 °C, at strain rate 10^{-4} s^{-1}	66
Fig. 3.11	Dislocation configuration in the region of DSA, at 250 °C, at strain rate 10^{-4} s^{-1}	67
Fig. 3.12	Dislocation configurations developed in the region of DSA, at temperature 350 °C, at strain rate 10^{-4} s^{-1}	68
Fig. 3.13	Dislocation configurations developed at 450 °C, above the region of DSA, at strain rate 10^{-4} s^{-1}	68
Fig. 3.14	Fractographs of the sample tested at RT at strain rate 10^{-4} s^{-1} : (a) full view, (b) magnified view of central region (Arrow indicates faceted regions)	69
Fig. 3.15	Fractographs showing fracture surfaces of the samples	70

	tested: (a) 200 °C, (b) 350 °C, (c) 450 °C, (d) 600 °C at strain rate 10^{-4} s^{-1}	
Fig. 3.16	Fractographs of the fibrous zones of the samples tested at: (a) 200 °C, (b) 350 °C, (c) 450 °C, (d) 600 °C at strain rate of 10^{-4} s^{-1}	71
Fig. 3.17	Variation of internal friction of the modified 9Cr–1Mo steel with temperature in normalized & tempered and, 5% and 10% cold rolled condition	72
Fig. 3.18	Tensile engineering stress strain curve of the 5% cold worked modified 9Cr–1Mo steel tested at 300 °C, at strain rate of 10^{-4} s^{-1} , showing smooth curve without serrations	77
Fig. 4.1	Effect of temperature on strength and elongation in normalized and tempered (N ₁ +T) condition	82
Fig. 4.2	Overall fracture surfaces showing the effect of test temperature on the nature of longitudinal splitting (a) 100 °C, (b) 80 °C, (c) 50 °C, (d) 30°C, (e) RT, (f) 13 °C, (g) 0 °C, (h) -50 °C and (i) -70 °C	84
Fig. 4.3	Magnified view of central fibrous zones of the specimens tested at different temperatures (a) 100 °C (b) 80 °C, (c) 0 °C, & (d) -50 °C	85
Fig. 4.4	Magnified view of petal shaped region of the specimens tested at different temperatures (a) 80 °C, (c) 0 °C, & (d) -70 °C	86
Fig. 4.5	Effect of specimen orientation with respect to rolling direction on: (a) yield strength and ultimate tensile strength, (b) total elongation	87
Fig. 4.6	Effect of the specimen orientation with respect to rolling direction on rosette fracture (a) along rolling direction (b) at 45 ° to the rolling direction (c) at 90 ° to the rolling direction	88
Fig. 4.7	SEM micrographs showing microstructures of the specimens in different heat treated conditions (a) A, (b) N ₁ +T (As supplied), (c) N ₂ +T, (d) N ₂ , (e) S ₂ +WQ	90
Fig. 4.8	Fracture surfaces of the specimens in different heat treated	91

	conditions: (a) A, (b) N ₂ , (c) S ₂ +WQ & (d) N ₂ +T	
Fig. 4.9	Fracture surfaces of normalized and tempered specimens tested in tension at RT at three different strain rates: (a) 10 ⁻² s ⁻¹ , (b) 10 ⁻³ s ⁻¹ , and 10 ⁻⁴ s ⁻¹	92
Fig. 4.10	Overall view of fracture surfaces of flat tensile specimens of different thicknesses: (a) 1.75 mm, (b) 2.4 mm, and (c) 4.5 mm	93
Fig. 4.11	Orientation distribution function (ODF) corresponding to $\phi_2 = 45^\circ$ section as obtained from the macrotexture examination of different heat treated specimens: (a) N ₁ +T, (b) A, (c) N ₂ , (d) S ₂ +WQ, and (e) S ₂ +WQ+T	96
Fig. 4.12	Longitudinal sections of tensile specimens of N ₁ +T, interrupted at different stages of deformation: (a) at maximum tensile load of 11 kN, (b) in necked region at 7 kN load, (c) fractured specimen at 6 kN load, (d) magnified view of (c), (e) showing linkage of voids along prior austenite grain boundaries. Tensile axis direction is shown by arrow.	98
Fig. 4.13	Cleavage fracture resulting from longitudinal splitting of N ₁ +T specimen tested in tension	99
Fig. 4.14	Longitudinal sections of the fractured tensile specimens of different heat treated specimens: (a) A, (b) N ₂ , (c) S ₂ +WQ	101
Fig. 4.15	Schematic of rosette fracture in N ₁ +T condition of the modified 9Cr-1Mo steel at RT (a) initial microstructure in unloaded condition, (b) voids formed at second phase particles on tensile loading in the region of necking, (c) easy linkage of voids lying along longitudinal grain boundaries, (d) triaxial stresses acting in the necked region of the specimen, & (e) rosette fracture	103
Fig. 5.1	Variation of stress amplitude with number of cycles at different strain rates of (a) 10 ⁻² s ⁻¹ , (b) 10 ⁻³ s ⁻¹ & (c) 10 ⁻⁴ s ⁻¹	106
Fig. 5.2	Dependence of fatigue life (as reversals to failure) with plastic strain amplitude, at strain rates of 10 ⁻² s ⁻¹ & 10 ⁻³ s ⁻¹	107
Fig. 5.3	LCF plots based on plastic strain energy and reversals to	110

	failure ($2N_f$) at strain rates of 10^{-2} s^{-1} & 10^{-3} s^{-1}	
Fig. 5.4	Stress–strain hysteresis loops translated to a common point of maximum compressive stress exhibiting Masing and non–Masing behavior at three different strain rates: (a) 10^{-2} s^{-1} , (b) 10^{-3} s^{-1} and (c) 10^{-4} s^{-1}	111
Fig. 5.5	Dislocation configurations resulting from LCF at strain rate of 10^{-2} s^{-1} at different strain amplitudes: (a, b) $\pm 0.25\%$, (c, d) $\pm 0.375\%$, (e, f) $\pm 0.50\%$. Formation of cell structure may be seen at all the strain amplitudes	114
Fig. 5.6	Dislocation configurations resulting from LCF at different strain amplitudes at the lowest strain rate of 10^{-4} s^{-1} : (a, b) $\pm 0.375\%$; (c, d) $\pm 0.50\%$.	115
Fig. 5.7	Variation of cell size with strain amplitude, in fatigue tested samples at strain rate of 10^{-2} s^{-1}	115
Fig. 5.8	Fracture surfaces of fatigue samples tested at RT, at strain rate of 10^{-2} s^{-1} at different strain amplitudes: (a, A) $\pm 0.25\%$ (b, B) $\pm 0.375\%$ & (c, C) $\pm 0.50\%$. The regions of fatigue fracture from surface towards interior are marked by black ink. Striations and secondary cracking are shown in the higher magnification images. Crack propagation direction is shown by white arrows.	117
Fig. 5.9	Low magnification fractographs of the LCF tested samples at strain rate of 10^{-3} s^{-1} at different strain amplitudes: (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, (c) $\pm 0.50\%$. Fatigue regions are marked by black ink and ratchet lines are shown by white arrows	118
Fig. 5.10	Crack initiation regions resulting from LCF at strain rate of 10^{-3} s^{-1} at different strain amplitudes (a) $\pm 0.25\%$, (b) $\pm 0.50\%$	119
Fig. 5.11	Fractographic images of LCF sample tested at $\pm 0.25\%$ at strain rate of 10^{-3} s^{-1} showing (a) tire marks, (b) faceted features	119
Fig. 5.12	TEM micrograph showing interaction between precipitates (MX) and dislocations in the sample tested in LCF at strain	121

	rate of 10^{-3} s^{-1} and strain amplitude of $\pm 0.25\%$	
Fig. 5.13	Schematic of the hysteresis loop illustrating the different components of stress for calculation of friction and back stress	123
Fig. 5.14	Variation of friction and back stress with number of cycles at different strain amplitudes at strain rate of 10^{-2} s^{-1} : (a) friction stress & (b) back stress	124
Fig. 5.15	Variation of friction and back stress with number of cycles at different strain amplitudes at strain rate of 10^{-3} s^{-1} : (a) friction stress & (b) back stress	125
Fig. 5.16	Variation of friction and back stress with number of cycles at different strain amplitudes at strain rate of 10^{-4} s^{-1} : (a) friction stress & (b) back stress	125
Fig. 6.1	Variation of cyclic stress with number of cycles for different strain amplitudes at different strain rates: (a) 10^{-2} s^{-1} , and (b) 10^{-3} s^{-1} .	132
Fig. 6.2	Effect of strain rate on cyclic stress response at strain amplitude of $\pm 0.50\%$.	132
Fig. 6.3	Coffin–Manson plot at strain rates of 10^{-2} s^{-1} and 10^{-3} s^{-1} at $300 \text{ }^\circ\text{C}$	133
Fig. 6.4	Translated hysteresis loops to a common point of maximum compressive stress showing non–Masing behavior at the lowest strain amplitude of $\pm 0.25\%$ and Masing behavior at high strain amplitudes ($\geq \pm 0.375\%$)	135
Fig. 6.5	Dislocation substructure of the specimens tested at strain rate of 10^{-2} s^{-1} for different strain amplitudes: (a) tested at $\pm 0.25\%$, (b) $\pm 0.375\%$, & (c) $\pm 0.50\%$	136
Fig. 6.6	Bright field TEM micrograph showing dislocation configuration resulting from LCF test at strain rate of 10^{-3} s^{-1} at strain amplitudes of (a) $\pm 0.375\%$, (b) $\pm 0.50\%$.	137
Fig. 6.7	Fracture surface of the fatigue specimens tested at strain rate of 10^{-2} s^{-1} at strain amplitudes of (a) $\pm 0.25\%$, and (b) $\pm 0.50\%$.	138

Fig. 6.8	Fracture surface of the fatigue specimen tested at strain rate of 10^{-3} s^{-1} at strain amplitudes of (a) $\pm 0.25\%$, and (b) $\pm 0.50\%$.	138
Fig. 6.9	Magnified view of the crack propagation region at strain rate of 10^{-2} s^{-1} at different strain amplitudes: (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, & (c) $\pm 0.50\%$	139
Fig. 6.10	Magnified view of the crack propagation region at strain rate of 10^{-3} s^{-1} at different strain amplitudes: (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, & (c) $\pm 0.50\%$	140
Fig. 6.11	Tire marks at strain amplitude of $\pm 0.50\%$ at low strain rate of 10^{-3} s^{-1}	141
Fig. 6.12	Bright field TEM micrographs of the specimen tested at strain amplitude of $\pm 0.375\%$ at strain rate of 10^{-3} s^{-1} showing dynamic recovery	142
Fig. 6.13	Bowing of dislocations may be seen from the specimen tested at strain amplitude of $\pm 0.375\%$ at strain rate of 10^{-3} s^{-1}	143
Fig. 7.1	Effect of strain amplitude on cyclic stress response of modified 9Cr–1Mo steel at different strain rate: (a) 10^{-2} s^{-1} (b) 10^{-3} s^{-1} at $600 \text{ }^\circ\text{C}$	148
Fig. 7.2	Effect of strain rate on cyclic stress response at strain amplitudes of $\pm 0.25\%$ & $\pm 0.50\%$	148
Fig. 7.3	Coffin–Manson plot of modified 9Cr–1Mo steel in normalized and tempered condition at $600 \text{ }^\circ\text{C}$ at strain rates of 10^{-2} s^{-1} & 10^{-3} s^{-1}	149
Fig. 7.4	Bright field TEM micrographs of the modified 9Cr–1Mo steel fatigue tested at strain rate of 10^{-2} s^{-1} at strain amplitudes: (a) $\pm 0.25\%$, (b) ± 0.375 & (c) $\pm 0.50\%$	151
Fig. 7.5	Bright field TEM micrographs of the modified 9Cr–1Mo steel fatigue tested at strain rate of 10^{-3} s^{-1} at strain amplitudes: (a) ± 0.375 & (b) $\pm 0.50\%$	151
Fig. 7.6	Deformation behavior of fatigue specimens of modified 9Cr–1Mo steel tested at a strain rate of 10^{-2} s^{-1} at different strain amplitudes: (a) $\pm 0.375\%$, showing dynamic	152

recrystallization & (b) $\pm 0.42\%$ showing formation of sub-grain and dynamic recovery

- Fig. 7.7** Deformation behavior of fatigue specimen of modified 9Cr–1Mo steel tested at strain amplitude of $\pm 0.375\%$ at a strain rate of 10^{-2} s^{-1} (a) bright field image showing fringes due to grain rotation (b) corresponding diffraction pattern showing splitting of diffraction spot 153
- Fig. 7.8** (a) Fringes formed due to grain rotation in the sample tested at lower strain rate of 10^{-3} s^{-1} at strain amplitude of $\pm 0.50\%$, (b) splitting of the diffraction spot in the corresponding diffraction pattern 153
- Fig. 7.9** (a) Bright field TEM micrograph showing fragmentation of lath boundaries of the fatigue specimen tested at strain amplitude of $\pm 0.50\%$ at strain rate of 10^{-3} s^{-1} 154
- Fig. 7.10** Array of parallel dislocations in the fatigue specimen tested at strain amplitude of $\pm 0.50\%$ at strain rate of 10^{-3} s^{-1} at $600 \text{ }^\circ\text{C}$ 154
- Fig. 7.11** Fracture surface of the specimens tested at strain rate of 10^{-2} s^{-1} and strain amplitudes (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, (c) $\pm 0.50\%$ 155
- Fig. 7.12** Fracture surface of the specimens tested at strain rate of 10^{-3} s^{-1} and strain amplitudes (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, (c) $\pm 0.50\%$ 156
- Fig. 7.13** Magnified view of the crack propagation region of fracture surface of the specimens tested at strain rate of 10^{-2} s^{-1} and at strain amplitudes: (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, (c) $\pm 0.50\%$ 157
- Fig. 7.14** Magnified view of the crack propagation region of fracture surface of the specimens tested at strain rate of 10^{-3} s^{-1} and at strain amplitudes: (a) $\pm 0.25\%$, (b) $\pm 0.375\%$, (c) $\pm 0.50\%$ 158
- Fig. 7.15** (a) Oxidation induced cracking on the fracture surface of the fatigue specimen tested at strain amplitude of $\pm 0.50\%$ at strain rate of 10^{-3} s^{-1} (b) corresponding EDX 159
- Fig. 7.16** Variation of friction stress and back stress with number of 163

cycles for different strain amplitudes at strain rate of 10^{-2} s^{-1}
at 600 °C: (a) friction stress (b) back stress

Fig. 7.17 Schematic showing annihilation of dislocations

164