



भारतीय
प्रौद्योगिकी
संस्थान
काशी हिन्दू विश्वविद्यालय



INDIAN
INSTITUTE OF
TECHNOLOGY
BANARAS HINDU UNIVERSITY

DECLARATION BY THE CANDIDATE

I, "**Prajyoti Singh**", certify that the work embodied in this thesis is my own bona fide work and carried out by me under the supervision of "**Prof. Sandip Chatterjee**" from "**July 2015**" to "**July 2020**", at the "**Department of Physics**", Indian Institute of Technology (BHU), Varanasi. The matter embodied in this thesis has not been submitted for the award of any other degree/diploma. I declare that I have faithfully acknowledged and given credits to the research workers wherever their works have been cited in my work in this thesis. I further declare that I have not wilfully copied any other's work, paragraphs, text, data, results, *etc.*, reported in journals, books, magazines, reports dissertations, theses, *etc.*, or available at websites and have not included them in this thesis and have not cited as my own work.

Date:

Place: IIT (BHU), Varanasi

Signature of the student

(*Prajyoti Singh*)

CERTIFICATE BY THE SUPERVISOR

It is certified that the above statement made by the student is correct to the best of my/our knowledge.

Supervisor

Sandip Chatterjee
(Professor)

Signature of Head of Department



COPYRIGHT TRANSFER CERTIFICATE

Title of the Thesis: Magnetic Properties of Some Pyrochlore and Double Perovskite Systems

Name of the Student: Prajyoti Singh

Copyright Transfer

The undersigned hereby assigns to the Indian Institute of Technology (Banaras Hindu University) Varanasi all rights under copyright that may exist in and for the above thesis submitted for the award of the “*DOCTOR OF PHILOSOPHY*” .

Date:

Place: IIT (BHU), Varanasi

Signature of the Student

(*Prajyoti Singh*)

Note: However, the author may reproduce or authorize others to reproduce material extracted verbatim from the thesis or derivative of the thesis for author's personal use provided that the source and the Institute's copyright notice are indicated.

Acknowledgements

My PhD life would not have been the same without the guidance and supervision of my supervisor **Prof. Sandip Chatterjee**, your mentorship has been a privilege. Your incredible vision for what shapes the future of the field scientifically, your passion for pursuing and uncovering new frontiers, and your work ethics and focus have all taught me an immense deal. I have learned from you to keep moving forward and trying after failure, to remain open to challenges, and to hold high standards in work. Therefore, I would like to express my deep gratitude to Prof. Sandip Chatterjee for his valuable and constructive suggestions during the research work. I will always remain thankful to him.

I express my gratitude to my RPEC members, **Dr. Shail Upadhyay, Dr. P. K. Roy** for their valuable, inspiration and numerous insightful suggestions during the entire course of this research.

I express my thankfulness to the **Prof. Debaprasad Giri, Prof. Prabhakar Singh** (Head of Department) for providing me required facilities of the department. I also wish to thank all other faculty members of the Department of Physics, IIT (BHU) Varanasi for motivation, unselfish support and suggestions during the course of my Ph.D.

I am also grateful to **Prof. A. K. Ghosh**, Department of Physics, Banaras Hindu University for his help which made it easy for me to work in such an inter-disciplinary subject.

I want to express my deepest grateful to my parents, and my younger brother for their support, love and care during my Ph.D. journey.

I would also like to express my extreme gratefulness towards my senior research members Dr. S. Kumar, Dr. K.K. Shukla, Dr. A. Singh, Dr. R. Singh, Dr. P. Gupta, Dr. S. Ghosh, Dr. A. Pal and other lab members Mr. V.K. Gangwar, Ms. P. Maiti, Ms. M. Singh, Mohd. Alam, Mrs. Labanya Ghosh, Mr. S. Vijay, Ms. Srishti, Mr. Rahul, Mr. Dheeraj, Ms. D. Pal, Ms. K. Anand, Ms. Seema, and Mr. Sambhab for sharing their knowledge and creating enjoyable lab atmosphere. I would also like to thank all research colleagues of Department of Physics, IIT (BHU), and Special thanks to my friends Mrs. R. Bala, Mr. V.P. Yadav, Mr. D. Yadav and Ms. R. Solanki for their awesome and pleasant company and confidence to complete my work with a 'smile'.

I am also thankful to all the technical, non-teaching as well as office staffs of the Department of Physics, IIT (BHU) Varanasi for their assistance when needed.

Last but not least, I wish to thank all my friends and the persons whose names have not been included on this piece of paper for extending their cooperation directly or indirectly.

In the end, I'd like to say 'Thank you' to Almighty for giving me patience to make this endeavor a success.

Sincerely

(Prajyoti Singh)

DEDICATED
TO
MY FAMILY

Contents

Certificate.....	i
Declaration by the Candidate.....	ii
Certificate by the Supervisors.....	ii
Copyright Transfer Certificate.....	iii
Acknowledgement	iv
Contents.....	vii
List of Figure.....	xi
List of Table.....	xx
Preface.....	xxii
Chapter 1 Introduction.....	27-74
1.1 Magnetism : Introduction.....	29
1.1.1 Diamagnetism.....	29
1.1.2 Paramagnetism.....	30
1.1.3 Ferromagnetism.....	31
1.1.4 Antiferromagnetism.....	31
1.1.5 Ferrimagnetism.....	32
1.2 Rules define the different types of magnetic ordering.....	32
1.2.1 Curie-Weiss Law.....	32
1.2.2 Mean field theory	33
1.2.3 Heisenberg Model.....	34
1.2.4 Ising Model	35
1.2.5 Landau theory of phase transition	35
1.3 Spin Frustration.....	36
1.3.1 Geometrical Spin Frustration.....	36
1.3.1.1 Pyrochlore oxide materials.....	40
1.3.1.1.1 Long range ordered.....	44
1.3.1.1.2 Spin Liquid	44
1.3.1.1.3 Spin Ice.....	44
1.3.1.1.4 Spin Glass.....	46

1.3.2 Disorder driven Spin Frustration	46
1.3.2.1 Single Perovskite Material.....	46
1.3.2.2 Double Perovskite Material	47
1.4 Literature survey on $A_2Ti_2O_7$ type Pyrochlore materials	49
1.5 Literature survey on A_2CoFeO_6 type Double Perovskite.....	55
1.6 Different Physical Phenomena related to our research.....	60
1.6.1 Spin relaxation or Spin freezing Process.....	60
1.6.2 Dzyaloshinsky-Moriya (DM) interaction.....	63
1.6.3 Spin-glass/ Cluster glass phenomenology	64
1.6.4 Exchange Bias (EB) effect.....	67
1.6.5 Magneto-dielectric coupling.....	70
1.6.6 Transport Property.....	71
1.6.6.1 Variable Range Hopping (VRH) Model.....	71
1.6.6.2 Arrhenius law.....	71
1.7 Motivation of the thesis.....	72
Chapter 2 Experimental Procedure.....	75-97
2.1 Sample Synthesis.....	77
2.1.1 Solid State Reaction Route.....	77
2.2 Experimental characterization techniques and their working principles	78
2.2.1 Characterization tools for structural property study	79
2.2.1.1 X-Ray Diffraction (XRD) technique	79
2.2.1.2 Raman Spectroscopy.....	81
2.2.1.3 Neutron Powder Diffraction (NPD) technique	84
2.2.1.4 X-ray Photoemission Spectroscopy (XPS) technique.....	87
2.2.1.5 X-ray Absorption Spectroscopy (XAS) technique	90
2.2.2 Characterization tools for magnetic property study.....	92
2.2.2.1 Magnetic Property Measurement System (MPMS): SQUID-VSM	92
2.2.3 Characterization tools for Dielectric study.....	95
2.2.3.1 Dielectric analysis.....	95

2.2.3.2 Magneto-Dielectric Analysis.....	96
Chapter 3 Spin freezing and Field induced transition in $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$: A Magnetic Property study.....	99-120
3.1 Introduction	101
3.2 Experiment	103
3.3 RESULTS AND DISCUSSION	104
3.3.1 Stability Study.....	104
3.3.2 Structural Study	105
3.3.3 Raman Study.....	106
3.3.4 DC Magnetic Study.....	108
3.3.5 AC Magnetic Study.....	112
3.4 Conclusion.....	120
Chapter 4 Wasp - Waisted loop and Spin frustration in $\text{Dy}_{2-x}\text{Eu}_x\text{Ti}_2\text{O}_7$ Pyrochlore....	121-143
4.1 Introduction.....	123
4.2 Experimental detail	125
4.3 RESULTS AND DISCUSSION	126
4.3.1 Stability and Structural Analysis.....	126
4.3.2 Raman Spectroscopy Analysis.....	128
4.3.3 Magnetization Analysis	130
4.3.3.1 DC magnetic Study.....	130
4.3.3.2 AC magnetic Study.....	137
4.4 Conclusion.....	143
Chapter 5 Roles of Re-entrant Cluster glass state and Spin lattice coupling in magneto-dielectric behavior of giant dielectric double perovskite $\text{La}_{1.8}\text{Pr}_{0.2}\text{CoFeO}_6$	145-163
5.1 Introduction	147
5.2 Experiment	148
5.3 Results	149
5.3.1 Stability and Structure Study	149
5.3.2 XAS Study	150
5.3.3 Magnetic Study	151
5.3.4 Dielectric Study	156

5.3.5	Resistivity Study	157
5.3.6	Magneto-dielectric Study	158
5.4	Conclusion.....	162
Chapter 6	Double glassy states and large spontaneous and conventional exchange bias effect in $\text{La}_{1.5}\text{Ca}_{0.5}\text{CoFeO}_6$ double perovskite.....	165-191
6.1	Introduction	167
6.2	Experimental details.....	169
6.3	Results and discussion.....	170
6.3.1	Stability and Structure Analysis.....	170
6.3.2	X-ray photoelectron spectroscopy (XPS) Analysis	172
6.3.3	Theoretical Analysis	175
6.3.4	Temperature dependent Neutron diffraction Analysis.....	177
6.3.5	Magnetic Analysis	180
6.4	Conclusion.....	190
Chapter 7	Conclusions and Future scopes.....	193-197
7.1	Conclusion of the thesis	195
7.2	Future Plans.....	196
References	198-241
List of publications.....		242-245

List of Figure

Figure 1.1 Schematic representation of spin alignment in diamagnetic and paramagnetic materials microscopic structures at rest and in the presence of a magnetic field H.....	31
Figure 1.2 Schematic representation of spin alignment in ferromagnetic, antiferromagnetic and ferrimagnetic materials.	32
Figure 1.3 Temperature variation of inverse magnetic susceptibility for paramagnetic, ferromagnetic and antiferromagnetic material.....	33
Figure 1.4 (a) Variation of free energy with magnetization. (b) Variation of Magnetization as a function of temperature. [Courtsey: Stephen Blundell, Magnetism in condensed matter; Oxford master series in condensed matter physics]	34
Figure 1.5 Direction of Ising spins on the vertices of 2 d triangular lattice illustrates geometrical spin frustration in which two spins are align antiferromagnetically where as the direction of third spin is not definite.....	37
Figure 1.6 Direction of Ising spins on the vertices of 2 d triangular lattice illustrates geometrical spin frustration in which two spins are align antiferromagnetically where as the direction of third spin is not definite.....	38
Figure 1.7 Examples of some possible geometrically frustrated magnetic lattices along with their space groups. The top two examples are of two dimensional frustrating lattice geometries, the bottom two examples are of two dimensional frustrating lattice geometries.....	39
Figure 1.8 Shows the Conventional unit cell of the corner-sharing tetrahedral $A_2B_2O_7$ pyrochlore structure with A^{3+} and B^{4+} sublattices.)	40

Figure 1.9 Shows the Conventional unit cell of $A_2B_2O_7$ pyrochlore structure with the arrangement of O and O' ion.....	41
Figure 1.10 Shows the pyrochlore lattice posses alternating kagome and triangular planar layers stacked along [111] direction [4]......	42
Figure 1.11 Shows the structural stability map for $A_2B_2O_7$ Pyrochlore.[4]	43
Figure 1.12 Showing the ‘two-in, two-out’ arrangement as A) In water ice between oxygen (large circle) and Hydrogen atom (black sphere). B) Ice rule follow in a single tetrahedral C) The cubic unit cell of spin ice pyrochlore lattice in which white sphere directs to spins into a ‘downward’ towards tetrahedra, while black sphere directs to spins ‘upwards’ towards tetrahedral [12]......	45
Figure 1.13 Show the crystal structure of ABX_3 perovskite.....	47
Figure 1.14 Describe the Double Perovskite unit cell structure formed by two perovskite unit cell. In this figure, blue sphere denotes A-site ion, violet sphere denotes B-site ion and yellow sphere presents B'-site ion.....	48
Figure 1.15 Shows the ground state spin configuration achieved for $Er_2Ti_2O_7$ [32]......	49
Figure 1.16 Showing the all in-all out spin arrangement in $Sm_2Ti_2O_7$	54
Figure 1.17 The frequency varying real and imaginary part of χ . χ_T and χ_S occur at lowest and highest frequencies respectively. Inset of fig.1.17 demonstrate the phasor diagram of χ . Here, ψ is the phase difference.....	62
Figure 1.18 Shows the DM interaction between two neighboring spins.....	63
Figure 1.19 Depicts the spin arrangement in ferromagnetic, antiferromagnetic and spin glass state.....	65
Figure 1.20 Depicts the arrangement of spins in spin glass state and cluster glass state.....	66
Figure 1.21 Represents the symmetric and asymmetric hysteresis loop in M-H curve.....	67

Figure 1.22 Shows the schematic explanation of exchange Bias effect.....	69
Figure 1.23 Shows the $\ln\rho$ versus $(1/T)^{0.25}$ curve with VRH fit (blue colour).....	71
Figure 1.24 (a) Shows the $\ln\rho$ versus $(1/T)$ curve with Arrhenius fit (green colour). (b) Shows the activation energy and the band gap between valence and conduction bands.....	72
Figure 2.1 Flow chart showing the steps of solid state reaction method.....	78
Figure 2.2 Schematic diagram of Bragg's law.....	80
Figure 2.3 Picture of Rigaku-MiniFlex-II DESKTOP powder X-ray diffractometer.	81
Figure 2.4 Energy level diagram of Rayleigh scattering and Raman Scattering.....	83
Figure 2.5 Renishaw Micro Raman Spectrometer.....	84
Figure 2.6 Setup of PD-2 (Powder Diffractometer-2) located at Bhabha Atomic Research, Mumbai, India.....	87
Figure 2.7 (a) Shows the photoelectric effect. (b) Depicts the schematic representation of XPS set up.....	89
Figure 2.8 Transition between the core levels which rise to XAS edges	91
Figure 2.9 Block diagram of XAS beam line consists of various components	92
Figure 2.10 Quantum Design MPMS 3 magnetometer	95
Figure 2.11 Magneto-dielectric measurement set up.....	97
Figure 3.1 Powder x-ray diffraction pattern for the $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ samples. Inset (i) Diffraction peak (222) of $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ samples. Inset (ii) Rietveld refinement for the $\text{Tb}_{1.0}\text{Eu}_{1.0}\text{Ti}_2\text{O}_7$ sample.	106
Figure 3.2 (a) Raman Spectra of the $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ samples at 300 K. (b) Variation of all four active phonon modes as a function of x in $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ samples ..	108

Figure 3.3 (a) The temperature dependent magnetization (ZFC) of the $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ samples. (b) $M(H)$ at 2 K for all TETO samples. Inset: Variation of effective magnetic moments with Eu content (x) derived from Curie–Weiss Law at high temperature for TETO sample. (c) The inverse DC susceptibility of $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ samples. (d) High Temperature Series Expansion fit for $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ ($x = 0.90, 0.95, 1.0$) samples. Inset: Curie–Weiss fit for $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ ($x = 0, 0.25, 0.50$) samples..... 112

Figure 3.4 (a): $\chi'(T)$ of $\text{Tb}_2\text{Ti}_2\text{O}_7$ ($f = 300, 500, 700$ Hz) and YTTO ($f = 500$ Hz) at zero applied DC field. Inset (i) $\chi''(T)$ of $\text{Tb}_2\text{Ti}_2\text{O}_7$. Inset (ii) $\chi''(T)$ of TTO and YTTO compounds at $H = 0$ Oe (500 Hz). (b) $\chi''(f)$ at different temperatures for $\text{Tb}_2\text{Ti}_2\text{O}_7$. Inset: Normalized χ'' as a function of f/f_{peak} and fitted theoretically (red) by Casimir du pre relations at and near the transition temperature for $\text{Tb}_2\text{Ti}_2\text{O}_7$ 113

Figure 3.5. (a) $\chi'(T)$ of all TETO compounds measured at $H = 0$ Oe ($f = 500$ Hz). Inset: $\chi'(T)$ of ETO at $H = 0$ Oe. (b) $\chi''(T)$ of all TETO compounds measured at $H = 0$ Oe ($f = 500$ Hz). Inset: $\chi''(T)$ of ETO at $H = 0$ Oe..... 115

Figure 3.6 $\chi'(T)$ (upper panel) and $\chi''(T)$ (lower panel) of TETO compounds at applied field of 10 kOe. (a) $x = 0.0$, (b) $x = 0.5$, (c) $x = 0.95$, (d) $x = 1.0$. The inset in every upper panel: $d\chi'(T)/dT$ with T . Marked by arrow are: Single ion spin freezing peak (T_f) and Single moment saturation peak (T^*)..... 117

Figure 3.7(a) The Arrhenius Fit of (T_f) peak for compounds $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ ($x = 0.25, 0.50, 0.90, 0.95$). Inset: Arrhenius Fit of $\text{Tb}_2\text{Ti}_2\text{O}_7$. (b) Variation of field induced transition temperature T^* with Eu content (x) for TETO samples..... 119

Figure 4.1 The lattice constant (Cubic Structure) of $Dy_{2-x}Eu_xTi_2O_7$ as a function of x value. Inset (i): X-ray powder diffraction pattern for the $Dy_{2-x}Eu_xTi_2O_7$ samples. Inset (ii): Rietveld refinement for the $Dy_{1.0}Eu_{1.0}Ti_2O_7$ sample..... 128

Figure 4.2. Raman spectra of the $Dy_{2-x}Eu_xTi_2O_7$ samples at 300 K. Inset: Variation of four active phonon modes as a function of x in $Dy_{2-x}Eu_xTi_2O_7$ samples along with the straight horizontal dashed lines for reference. 129

Figure 4.3. The temperature dependent DC magnetic susceptibility (ZFC) with standard Curie-Weiss fit of the x = 0.0, 0.5, 1.0 samples. Inset (i): The temperature dependent DC magnetic susceptibility (ZFC) with standard Curie-Weiss fit of the x = 1.5, 1.8, 1.9 samples. Inset (ii): χ vs. T curve of x = 2.0 sample with standard CW fit. (b): Inverse DC susceptibility vs. T curve of $Dy_{2-x}Eu_xTi_2O_7$ compounds with inverse CW fit at (100-300 K). (c): High temperature series expansion fit for $Dy_{2-x}Eu_xTi_2O_7$ (x = 1.5, 1.8, 1.9, 2.0) samples. (d): Variation of derived CW temperature with x value of $Dy_{2-x}Eu_xTi_2O_7$ series from (2-20 K) CW fit. Inset: Variation of calculated effective magnetic moments with Eu content (x) derived from inverse CW fit at high temperature (100-300 K) for DETO samples.. 131

Figure 4.4 Zoom part of M-H curve for x = 1.5, 1.8, 1.9 samples at 2 K. Inset: M-H curves at 2 K for all DETO samples. (b): Variation of $d^2\delta M/dH^2$ curve with applied H at 2 K for x = 1.5 sample. {Zoom part of 4.4(b)} - $d^2\delta M/dH^2$ curve with applied H (0.4-1.0 T) at 2 K for x = 1.5 sample. Inset: δM between ascending and descending portions of M-H curve for x = 1.5 sample. {Zoom part of inset 4.4(b)}- δM of M-H curve for x = 1.5 sample from 0.25-0.75 T. (c): Variation of $d^2\delta M/dH^2$ curve with applied H at 2 K for x = 1.8, 1.9 samples. Inset: δM between ascending and descending portions of M-H curves for x = 1.8, 1.9 samples. (d): Descending first

quadrant M-H curve for $x = 1.5, 1.8, 1.9$ samples with LA fit above 1 T.....	134
Figure 4.5 $\chi'(T)$ of $x = 0.0, 0.5, 1.0$ for $f = 500$ Hz at zero applied DC field. Inset (i): $\chi'(T)$ of $x = 1.5, 1.8, 1.9$ for $f = 500$ Hz at zero applied DC field. Inset (ii): $\chi'(T)$ of $x = 2.0$ for $f = 500$ Hz at zero applied DC field. (b): $\chi''(T)$ of $x = 0.0, 0.5, 1.0$ for $f = 500$ Hz at zero applied DC field. Inset (i): $\chi''(T)$ of $x = 1.5, 1.8, 1.9$ for $f = 500$ Hz at zero applied DC field. Inset (ii): $\chi''(T)$ of $x = 2.0$ for $f = 500$ Hz at zero applied DC field.....	138
Figure 4.6 $\chi'(T)$ (upper panel) and $\chi''(T)$ (lower panel) of $Dy_{2-x}Eu_xTi_2O_7$ compounds at applied field of 2 T. (a): $Dy_{1.5}Eu_{0.5}Ti_2O_7$, (b): $Dy_{1.0}Eu_{1.0}Ti_2O_7$, (c): $Dy_{0.5}Eu_{1.5}Ti_2O_7$, (d): $Dy_{0.2}Eu_{1.8}Ti_2O_7$, (e): $Dy_{0.1}Eu_{1.9}Ti_2O_7$. Marked by arrow are: Single ion spin freezing peak of Dy^{3+} ions (T_f) and Single ion spin freezing peak of Eu^{3+} ions (T_s).....	140
Figure 4.7 The Arrhenius Fit of (T_f) peak for ($x = 0.5, 1.0, 1.5, 1.8, 1.9$) compounds and Arrhenius Fit of (T_s) peak for ($x = 1.5, 1.8, 1.9$) compounds.(b): Variation of derived E_a values of T_f and T_s peaks with x value of $Dy_{2-x}Eu_xTi_2O_7$.(c): Variation of T_f and T_s peaks with x value of $Dy_{2-x}Eu_xTi_2O_7$	141
Figure 5.1. The XRD pattern along with the Rietveld refinement of LPCFO at 300 K.....	150
Figure 5.2. XAS spectra of (a) Co edge (b) Fe edge recorded at 300K.....	151
Figure 5.3. (a) The temperature dependent ZFC and FC Curve of LPCFO at different magnetic fields. (b) The isothermal (M-H) curves of LPCFO at different temperatures. Inset: dM/dT as a function of temperature.....	152
Figure 5.4. The temperature dependent real $\chi'(T)$ (a) and imaginary $\chi''(T)$ (b) part of AC susceptibility of LPCFO at zero field. (c) Dynamic Scaling fit of $\log f$ Vs $\log (T_f/T_{SG} - 1)$. Inset :	

Vogel-Fulcher fit of $\ln f$ Vs $1/(T_f-T_0)$ curve. (d): TRM data at 25 K fitted with KWW equation.
..... 154

Figure 5.5 (a) Temperature dependent dielectric constant (ϵ') of LPCFO. Inset: Arrhenius fit of dielectric relaxation of LPCFO. (b) Temperature dependent dielectric tangent loss ($\tan\delta$) of LPCFO. Inset: a comparative plot of $\tan\delta(T)$ and imaginary part of dielectric function $\epsilon''(T)$ at 10 kHz frequency..... 156

Figure 5.6 (a) Temperature dependent resistivity $\rho(T)$ curve of LPCFO at zero magnetic field. (b) 3-d VRH fit of $\rho(T)$ at 120 – 190 K temperature range. (c) SPH fit of $\rho(T)$ at 240 – 300 K temperature range..... 158

Figure 5.7 (a): Magneto dielectric (%) as a function of magnetic field for LPCFO at different temperatures. Inset: Raw pictorial diagram of Magneto dielectric (%) Vs. temperature at 1.3 T magnetic field. (b) Raman scattering intensity of LPCFO at different temperatures (80-330 K) as a function of Raman shift. (c) Temperature dependence of the phonon positions of two typical modes (A_g and B_g) observed for LPCFO. Brown vertical dotted lines represent anomalies. (d) Temperature dependence of the Raman line widths (FWHM) of A_g and B_g modes. Blue dotted line shows the different slopes. Brown vertical dotted lines represent anomalies.....160

Figure 6.1 (a) The XRD pattern along with the Rietveld refinement of LCCFO at 300 K. (b) The Crystal structure of LCCFO sample using VESTA.....172

Figure 6.2 (a): The full XPS surface scan survey of LCCFO sample. Deconvoluted XPS Spectra of LCCFO (b) La 3d level, (c) Ca 2p level, (d) Co 2p level, (e) Fe 2p level and (f) O1s level.
.....175

Figure 6.3. (a) : TDOS of LCCFO system. (b): Spin resolved PDOS for La-f, Ca-d, Co-d, Fe-d, and O-p orbitals inset (i) PDOS of Co-d state. (ii) PDOS of Fe-d state.....176

Figure 6.4. (a): Rietveld refined neutron diffraction patterns at various temperatures of LCCFO system. The oval marked area indicates the purely magnetic (011) Bragg peak. (b): Magnetic structure of LCCFO from 6 K NPD data.....178

Figure 6.5 (a) : ZFC and FC curve of LCCFO sample at 100 Oe magnetic field. Inset : Temperature dependence of dM/dT for FC data at 100 Oe magnetic field. (b) Temperature dependence of the magnetization under ZFC protocol at $H = 100$ Oe, 1000 Oe and 10000 Oe. (c): Power-law fitting to the log-log plot of " $1/\chi$ Vs $((T-T_C^R)/T_C^R)$ " at 100 Oe ZFC data. Inset : Inverse susceptibility Vs temperature curve at 1000 Oe magnetic field with Curie-Weiss law fit. (d): $M(H)$ curves of LCCFO at different temperature. 183

Figure 6.6 Temperature dependence of the AC susceptibility of LCCFO at zero magnetic field. (a)Upper panel : The real part χ' and lower panel : The imaginary part χ'' from $T = 140-180$ K. (b)Upper panel : The real part χ' and lower panel : The imaginary part χ'' from $T = 2-50$ K. T_1 and T_s are the cluster glass temperature. (c) Dynamic Scaling fit of $\log f$ Vs $\log (T_f/T_{SG} - 1)$ curve. Inset : Vogel-fulcher fit $\ln f$ Vs $1/(T_f-T_0)$ data in the T_1 RCG region. (d) Dynamic Scaling fit of $\log f$ Vs $\log (T_f/T_{SG} - 1)$ curve. Inset : Vogel-fulcher fit of $\ln f$ Vs $1/(T_f-T_0)$ data in the T_s RCG region.....186

Figure 6.7 (a) ZFC $M(H)$ isotherms in the range ± 70 kOe at 5 K. (b) The $M(H)$ isotherms measured at 5 K after cooling the sample under +50 kOe (green curve) and -50 kOe (orange curve). (c): ZFC $M(H)$ isotherms in the range ± 20 kOe at 10 K, 20 K, 30 K and 40 K. Inset : ZFC $M(H)$ isotherms in the range ± 20 kOe at 50 K (d): ZFC $M(H)$ isotherms in the range ± 20 kOe at 60 K, 70 K, 80 K, 90 K and 100 K. (e): Variation of H_{EB} (left Y -axis) and H_C (right Y-

axis) with the temperature (10 – 90 K). (f): Variation of M_{SEB} (left Y –axis) and M_C (right Y-axis) with the temperature (10 – 90 K). 189

List of Table

Table 1.1 Shows the crystallographic positions of cubic $A_2B_2O_6O'$ Pyrochlore oxide having $Fd\bar{3}m$ space group symmetry.....	41
Table 1.2 Shows the characteristics of different $A_2Co/Mn/NiO_6$ type double perovskite materials.....	58
Table 3.1 The ionic radius ratio of TETO series compounds.....	105
Table 3.2 Lattice parameters obtained from rietveld refinement of all TETO compositions with Space Group $Fd-3m$	105
Table 3.3 Curie–Weiss temperature, theoretical and calculated magnetic moment of ($x = 0.00, 0.25, 0.50$) samples obtained from Curie–Weiss fit (25-300 K).....	109
Table 3.4 Theoretical and calculated magnetic moment of ($x = 0.90, 0.95$) samples obtained from Curie–Weiss (150-300 K) fit.....	110
Table 3.5 Curie–Weiss temperature, classical exchange energy, dipolar interaction energy and calculated magnetic moment of ($x = 0.90, 0.95, 1.0$) samples obtained from the fitting of the High Temperature Series Expansion [2-5 K].....	111
Table 4.1 The ionic radius ratio of DETO series compounds.....	127
Table 4.2 Extracted Curie–Weiss temperature, classical exchange energy, dipolar interaction energy and calculated magnetic moment of ($x = 1.5, 1.8, 1.9, 2.0$) samples by high temperature series expansion fit [2-5 K].....	132
Table 4.3 Extracted anisotropy constant (K_I) values of $x = 1.5, 1.8, 1.9$ samples.....	137
Table 6.1 Structural parameters obtained by Rietveld profile refinement of the powder XRD pattern for $La_{1.5}Ca_{0.5}CoFeO_6$ at 300K. (Monoclinic – $P2_1/n$).....	171

Table 6.2 The magnetic moment values of Co and Fe sublattices evaluated by NPD data at different temperatures180

Table 6.3 Fitted parameters obtained by dynamic scaling law and Vogel fulcher fit at T_1 and T_S temperatures.....185

Preface

Spin frustration or competing interactions between the interacting degree of freedom is one of the eternal and enlightened research area in condensed matter world. Geometrical Spin frustrated systems in which magnetic moments reside on corner sharing tetrahedra show multiple degenerate ground states. In such frustration mechanism, the systems do not maintain lowest energy state and switch to different magnetic ground states. Triangular lattice, kagome lattice and pyrochlore lattice are the name of some lattices which shows geometrical spin frustration. Particular, Pyrochlore material exhibits exotic physical and magnetic properties even at very low temperature. Generally, pyrochlore materials exhibit form $A_2B_2O_7$ type empirical formula in which A-site ion is rare earth elements and B-site elements are 3d transition elements. Among the Pyrochlore materials, Rare earth titanates ($R_2Ti_2O_7$) reveal different types of magnetic phases like $Tb_2Ti_2O_7$ as spin liquid, $Dy_2Ti_2O_7$ as spin ice, $Gd_2Ti_2O_7$ as long range ordered systems, $Eu_2Ti_2O_7$ as X-Y antiferromagnetically ordered systems and much more. Enrich in physics and utilization in real world make these materials important among geometrically frustrated systems.

Along with geometrical spin frustration, disorder driven spin frustration seeks unusual attention in recent times. When the disorder presents in a system causes the spin frustration among the structure, known as disorder driven spin frustration. The single perovskite and double perovskite which illustrates spin frustration due to presence of disorderness comes in the class of multifunctional materials. The double perovskite materials have an $A_2BB'O_6$ type empirical formula i.e. $ABO_3.AB'O_3$. One unit cell of double perovskite material consists of two unit cells of single perovskite materials. In this empirical formula A-site is generally alkaline or rare earth element and B and B'-site ions are 3d, 4d, 5d transition elements. The correlation between electrical and magnetic ordering at room temperature makes these materials more efficient and

applicable in many devices such as memory devices, magnetic sensors, magnetic recording media etc. Eventually, numerous dynamic properties and magnetic processes like presence of high temperature magnetic ordering, exchange-bias, spin glass/cluster glass, Griffith like phase, high dielectric constant with low loss tangent, large magneto-dielectric frame the double perovskite systems more efficient and promising. Although, $A_2Co/Mn/NiO_6$ type double perovskite materials have been widely investigated. Still, there is a large scope to flourish the characteristics of La_2CoFeO_6 type double perovskite compounds. Moreover, Rare earth element and hole doping at La site is one of the best way to intensify such alluring and unusual properties and prepared them into use of different practical applications.

Therefore, our research work is focused to enhance the ravishing properties of rare earth titanates and La_2CoFeO_6 type double perovskite materials. In present thesis, the structural, magnetic, transport and magneto-dielectric properties of spin frustrated systems have been investigated. As to provide systematic discussion, this thesis has been classified into seven chapters. Outline of each seven chapter is given below-

Chapter 1, In chapter 1, the introduction of magnetism along with different models which classifies the different type of magnetic ordering has been explained. With this, the theory and concepts of spin frustration with their related materials has also been discussed. Two types of spin frustration i.e. geometrical spin frustration and disorder driven spin frustration are addressed in this chapter. Brief introduction of Pyrochlore material, their different magnetic phases, physics of perovskite and double perovskite materials with their literature review have been elaborated in this chapter. Here, we have also discussed various important magnetic phenomenons like spin relaxation process, exchange-bias phenomenon, spin glass/cluster glass,

Dzyaloshinsky-Moriya (D-M) interaction etc. Moreover, different electrical transport models for conductivity are also discussed like variable range hopping model, Arrhenius model.

Chapter 2, This chapter contains the synthesis process involved in our research work. The basic principles and mechanism of different characterization tools which we have employed in our research work is also explained in this chapter. X-ray diffraction, Raman spectroscopy, neutron diffraction, X-ray absorption spectroscopy, X-ray photoemission spectroscopy techniques has been described the structure, phase and electronic state identity. The description of Quantum Design MPMS magnetometer has been given for magnetic analysis. Dielectric and magneto dielectric analysis is also included in this chapter.

Chapter 3, This chapter investigated the structural and magnetic properties of $(\text{Tb}_{1-x}\text{Eu}_x)_2\text{Ti}_2\text{O}_7$ pyrochlore compounds. All the ordered samples have cubic crystal structure with $Fd\bar{3}m$ space group. High series expansion fit on temperature dependent DC magnetic data reveals the presence of dipolar and exchange interactions in Eu rich samples. Spin liquid $\text{Tb}_2\text{Ti}_2\text{O}_7$ compound shows a partial spin freezing at ~ 33 K in presence of zero magnetic field. This partial spin freezing of $\text{Tb}_2\text{Ti}_2\text{O}_7$ compound is single ion spin freezing in nature. The AC magnetic susceptibility data observed this partial single ion spin freezing for all compounds. A single moment saturated field induced transition is observed for all compounds at low temperature in presence of 10 kOe magnetic field.

Chapter 4, This chapter presented the systematic structural, raman and magnetic study of $\text{Dy}_{2-x}\text{Eu}_x\text{Ti}_2\text{O}_7$ pyrochlore materials. A systematic shift in all phonon modes with higher Eu content in $\text{Dy}_{2-x}\text{Eu}_x\text{Ti}_2\text{O}_7$ observed in Raman spectra confirms the successful substitution of Dy^{3+} ion by Eu^{3+} ions. High concentration of Eu induces the exchange interactions between atoms and alters

the crystal-field interactions in $\text{Dy}_{2-x}\text{Eu}_x\text{Ti}_2\text{O}_7$. Rich Eu content samples ($x= 1.5, 1.8$ and 1.9) show the existence of wasp-waisted hysteresis loop which is explained on the basis of dipolar field, anisotropy exchange interaction and spin frustration present in the samples. Interestingly, AC susceptibility shows two single ion spin freezing transitions corresponding to Dy^{3+} and Eu^{3+} ions respectively in Eu rich samples only.

Chapter 5, This chapter deals with the effect of spin frustration due to disorder present in $\text{La}_{1.8}\text{Pr}_{0.2}\text{CoFeO}_6$ double perovskite sample. The compound was investigated by the X-ray diffraction, X-ray absorption spectroscopy, magnetic, dielectric (zero-field and in-field) and Raman spectroscopy techniques. The same oxidation state (+3) for Co and Fe ion is identified through XAS spectra. Above room temperature magnetic ordering with existence of re-entrant cluster glass state is analyzed by magnetic data. This Double perovskite sample is also renowned for magneto-dielectric coupling (MDC) which is observed in two temperature regions (25-80 K and 125-275 K). Presence of cluster glass at low temperature and spin lattice interaction at high temperature are the possible explanation of magneto-dielectric coupling. The resistivity measurement reveals its semiconducting nature which was explained by different conduction models. Eventually, huge dielectric constant and the low tangent loss make $\text{La}_{1.8}\text{Pr}_{0.2}\text{CoFeO}_6$ sample promising candidate from the application point of view.

Chapter 6, This chapter includes the , X-ray diffraction, X-ray photoemission spectroscopy (XPS), Neutron diffraction, magnetization measurements and density function theory calculations of double perovskite $\text{La}_{1.5}\text{Ca}_{0.5}\text{CoFeO}_6$ sample. A ferrimagnetic transition is observed at $T_C \sim 167$ K. The ferrimagnetic ground state is also confirmed by DFT and neutron powder diffraction. The presence of anti-site disorder (ASD) has also been demonstrated. Double re-entrant cluster glass transitions ($T_1 \sim 11$ K and $T_S \sim 35$ K) were observed which has been

attributed to the ASD effect. Both conventional and spontaneous exchange bias are observed in this double perovskite system. The observed values of large $H_{SEB} \sim 2.106$ kOe and giant $H_{CEB} \sim 1.56$ T at 5 K might be due to the coexistence of long range magnetic ordering and glassy state. The presence of double glassy states, large exchange bias effect and different magnetic phases make this system a potential candidate for spintronics applications.

Chapter 7, This chapter keeps the details of conclusion of our research work presented in this thesis. The brief glimpse of future research work has also added in this chapter.