

LIST OF FIGURES

| | Page |
|---|------|
| Figure 1.1: Stick and ball representation of ZnO crystal structures: (a) hexagonal wurtzite, (b) cubic zinc blende, and (c) cubic rocksalt. The shaded gray and black spheres denote Zn and O atoms, respectively. | 2 |
| Figure 1.2: The hexagonal wurtzite crystal structure of ZnO. One unit cell is outlined for clarity. | 4 |
| Figure 1.3: The Comparison of calculated electron drift velocity versus electric field for wurtzite structure ZnO (solid) and GaN (dashed) at 300 K. | 8 |
| Figure 2.1: Point defects in the heterogeneous ionic solid. | 20 |
| Figure 2.2: Schematic band diagram of near band edge (NBE) and defect band emission (DBE) in ZnO. | 21 |
| Figure 2.3: Variation in band gap of transition metal (TM= Cr, Mn, Fe, Co, & Ni) doped ZnO for $Zn_{0.95}TM_{0.05}O$ composition. | 31 |
| Figure 3.1: Flow chart of the synthesis of ZnO through co-precipitation technique. | 43 |
| Figure 3.2: Flow chart of the synthesis of ZnO through sol-gel technique. | 44 |
| Figure 3.3: Flow chart of the synthesis of ZnO through combustion technique. | 46 |
| Figure 3.4: Flow chart of the synthesis of Mg/Co doped or Mg and Co codoped ZnO through co-precipitation technique. | 48 |
| Figure 3.5: Flow chart of the synthesis of ZnO(%)- $SrAl_2O_4$ composite through combustion technique. | 50 |
| Figure 3.6: Schematic of diffraction of x-rays by a crystal. | 51 |
| Figure 3.7: Flowchart for PAL spectrometer. | 59 |
| Figure 3.8: Traps level in a crystal. | 60 |
| Figure 4.1: The XRD patterns of the ZnO powder synthesised at different pH (5.5, 7, 9, 10, 11.5 and 13.0), dried at 80 °C for 24 h. | 62 |

| | | |
|---------------------|--|----|
| Figure 4.2: | The XRD patterns of the ZnO powder synthesised at different <i>pH</i> (5.5, 7, 9, 10, 11.5 and 13.0), dried at 250 °C for 5 h. | 63 |
| Figure 4.3: | The SEM image of the ZnO powder synthesised at different <i>pH</i> (5.5, 7, 9, 10, 11.5 and 13.0) of precipitation and dried at 80 °C for 5 h. | 65 |
| Figure 4.4: | Schematic diagram of the growth of ZnO under coprecipitation route with varying the <i>pH</i> (5.5, 7, 9, 10, 11.5 and 13.0) of solution during synthesis. | 66 |
| Figure 4.5: | The Raman spectrum of the ZnO powder synthesised at different <i>pH</i> (5.5, 7, 9, 10, 11.5 and 13.0) and dried at 80 °C for 24 h. | 69 |
| Figure 4.6: | The Raman spectrum of the ZnO powder synthesised at different <i>pH</i> s (5.5, 7, 9, 10, 11.5 and 13.0) and dried at 250 °C for 5 h. | 71 |
| Figure 4.7: | The PL spectrum obtained by using the excitation wavelength 355 nm for the ZnO powder synthesised at different <i>pH</i> (5.5, 7, 9, 10, 11.5 and 13.0) (a) dried at 80 °C for 24 h, (b) dried at 250 °C for 5 h. | 73 |
| Figure 4.8: | The deconvoluted PL spectra of sample synthesised at <i>pH</i> 13 and dried at 80 °C for 24 h. | 74 |
| Figure 4.9: | Positron lifetime spectrum of ZnO powder synthesized at different <i>pH</i> of 9.0, 11.5 and 13.0 (a) dried at 80 °C for 24 h, (b) dried at 250 °C for 5 h. | 76 |
| Figure 4.10: | The XRD patterns of ZnO powder synthesised through sol-gel route and calcined at different temperatures (250, 600, 800, 1000 °C) for 5 h. | 79 |
| Figure 4.11: | W-H plot corresponding to XRD patterns of ZnO powder synthesised through sol-gel route and calcined at different temperatures (250, 600, 800, 1000 °C) for 5 h. | 80 |
| Figure 4.12: | The SEM image of the ZnO powder synthesised through sol-gel route and calcined at 1000 °C with (a) low resolution, (b) high resolution and the inset image shows the histogram of particle size distribution for the sample calcined at 1000 °C. | 81 |
| Figure 4.13: | The Raman spectrum of ZnO powder synthesised through sol-gel route and calcined at different temperatures (250, 600, 800, 1000 °C) for 5 h. | 82 |

| | | |
|---------------------|---|----|
| Figure 4.14: | The deconvoluted Raman spectrum of the sample synthesised through sol-gel route and calcined at 1000 °C for 5 h. | 83 |
| Figure 4.15: | The PL spectrum obtained by using the excitation wavelength 355 nm for the ZnO powder synthesised through sol-gel route and, calcined at different temperatures (250, 600, 800, 1000 °C) for 5 h. | 85 |
| Figure 4.16: | Positron annihilation lifetime spectrum of ZnO powder synthesised through sol-gel route and calcined at different temperatures (250, 600, 800, 1000 °C) for 5 h. | 86 |
| Figure 4.17: | The plot in between different calcination temperature and the calculated positron annihilation lifetime (a) τ_1 and τ_2 and (b) τ_{av} , for the sample synthesised through sol-gel technique. | 88 |
| Figure 4.18: | The TG-DTA of as prepared gelatinous sample of ZnO @ 10 °C/min. | 89 |
| Figure 4.19: | The XRD patterns of ZnO powder synthesised through combustion route and calcined at different temperatures (600, 800, 1000, and 1200 °C) for 5 hr. | 90 |
| Figure 4.20: | W-H plot corresponding to XRD patterns of ZnO powder synthesised through combustion route and calcined at different temperatures (600, 800, 1000 and 1200 °C) for 5 h. | 91 |
| Figure 4.21: | The SEM image of the ZnO powder synthesised through combustion route and calcined at (a) 600 °C and (b) 1200 °C. Inset shows the zoomed view of the encircled region. | 92 |
| Figure 4.22: | The histogram of the particle size distribution obtained from the SEM image of the ZnO powder synthesised through combustion route and calcined at (a) 600 °C and (b) 1200 °C. | 92 |
| Figure 4.23: | The Raman spectrum of ZnO powder synthesised through combustion route and calcined at different temperatures (600, 800, 1000, and 1200 °C) for 5 h. | 93 |
| Figure 4.24: | The deconvoluted Raman spectra of the samples synthesised through combustion route and calcined at (a) 600 °C and (b) 1200 °C) for 5 h. | 94 |
| Figure 4.25: | The PL spectrum obtained by using the excitation wavelength 355 nm for the ZnO powder synthesised through combustion route and calcined at different temperatures (600, 800, 1000 and | 95 |

1200 °C) for 5 h. Inset shows the deconvoluted PL spectra of the sample calcined at 1200 °C.

- Figure 4.26:** Positron annihilation lifetime spectrum of ZnO powder synthesised through combustion route, calcined at different temperatures (600, 800 and 1000 °C) for 5 h. 98
- Figure 4.27:** The proposed energy band diagram of the electron transfer in ZnO after excitation. 99
- Figure 5.1:** X-ray diffraction pattern of $Zn_{1-x}Mg_xO$ ($x = 0, 0.04, 0.08, 0.10, 0.12, 0.15$ and 0.20) nanoparticles. 103
- Figure 5.2:** Le-Bail refinements of X-ray diffraction pattern for $Zn_{1-x}Mg_xO$ ($x = 0, 0.04, 0.08, 0.12, 0.10$ and 0.15) nanoparticles. 103
- Figure 5.3:** W-H plot for $Zn_{1-x}Mg_xO$ ($x = 0, 0.04, 0.08, 0.10, 0.12$ and 0.15) nanoparticles. 104
- Figure 5.4:** Transmission Electron Micrograph of (a) ZnO and (b) $Zn_{0.96}Mg_{0.04}O$ nanoparticles with corresponding EDS spectra. Inset shows the SAED pattern of respective samples. 105
- Figure 5.5:** Photo luminescence spectrum of ZnO and $Zn_{0.96}Mg_{0.04}O$ nanoparticles. Inset shows the plot of $(\alpha hv)^2$ vs. hv of both samples obtained from UV-visible spectrum. 106
- Figure 5.6:** Raman spectrum of ZnO and $Zn_{0.96}Mg_{0.04}O$ nanoparticles in the range of 300 to 1400 cm^{-1} . Inset shows the Lorentzian fitting of 270-760 cm^{-1} and 900-1240 cm^{-1} for respective samples. 108
- Figure 5.7:** FT-IR transmittance spectrum of $Zn_{1-x}Mg_xO$ ($x = 0, 0.04, 0.08, 0.10, 0.12$ and 0.15) nanoparticles (left side). The absorbance plot for the ZnO and $Zn_{0.85}Mg_{0.15}O$ nanoparticles in range of 2500-3900 cm^{-1} , with Lorentzian fitting, is shown in right side. 109
- Figure 5.8:** Positron lifetime spectrum of ZnO and $Zn_{0.96}Mg_{0.04}O$ nanoparticles. 111
- Figure 5.9:** XPS spectrum of $Zn_{1-x}Mg_xO$ ($x = 0, 0.04, 0.08, 0.10, 0.12$ and 0.15) nanoparticles (a) For Zn 2p_{3/2} and 2p_{1/2}, (b) For Mg 1s and (c) For O 1s. 112
- Figure 5.10:** Le-Bail refinements of X-ray diffraction pattern for $Zn_{0.95}Co_{0.05}O$, $Zn_{0.96}Mg_{0.04}O$ and $Zn_{0.91}Co_{0.05}Mg_{0.04}O$ nanoparticles. 114

| | | |
|---------------------|--|-----|
| Figure 5.11: | FE-SEM micrograph with corresponding EDX spectra of (a) $Zn_{0.95}Co_{0.05}O$ (b) $Zn_{0.96}Mg_{0.04}O$ and (c) $Zn_{0.91}Co_{0.05}Mg_{0.04}O$ nanoparticles. | 116 |
| Figure 5.12: | Plot of $\alpha^2(h\nu)^2$ vs. $h\nu$ of $Zn_{1-x-y}Co_yMg_xO$ (a) $x=0.0$ and $y=0.0$ (b) $x = 0.04$ and $y=0.0$ (c) $x=0.0$ and $y = 0.05$ and (d) $x = 0.04$ and $y =0.05$. | 117 |
| Figure 5.13: | Normalised Raman spectra of $Zn_{0.95}Co_{0.05}O$, $Zn_{0.96}Mg_{0.04}O$ and $Zn_{0.91}Co_{0.05}Mg_{0.04}O$ nanoparticles. | 118 |
| Figure 5.14: | Lorentzian fitting for the Raman spectra of (a) ZnO , (b) $Zn_{0.95}Co_{0.05}O$, (c) $Zn_{0.96}Mg_{0.04}O$ and (d) $Zn_{0.91}Co_{0.05}Mg_{0.04}O$ nanoparticles. | 120 |
| Figure 5.15: | Temperature variation of magnetisation of the $Zn_{0.91}Co_{0.05}Mg_{0.04}O$ nanoparticles under field-cooling (FC) and zero-field-cooling (ZFC) conditions. | 123 |
| Figure 5.16: | (a) Magnetisation versus external magnetic field of $Zn_{0.91}Mg_{0.04}Co_{0.05}O$. (b) Inverse of magnetic susceptibility as a function of temperature, which is extrapolated to zero in the temperature axis. | 124 |
| Figure 5.17: | Positron lifetime spectra of $Zn_{0.95}Co_{0.05}O$, $Zn_{0.96}Mg_{0.04}O$ and $Zn_{0.91}Co_{0.05}Mg_{0.04}O$ nanoparticles. | 126 |
| Figure 6.1: | TGA-DTA of as prepared SAO and SAO(20) samples measured at $10^\circ C/min$. | 131 |
| Figure 6.2: | SEM image of SAO powder calcined at (a) $700^\circ C$ and (b) $1200^\circ C$ and SAO(20) composite powder calcined at (c) $700^\circ C$, (d) $1200^\circ C$. | 131 |
| Figure 6.3: | Normalised XRD patterns of SAO sample calcined at different temperatures in the range of $700-1200^\circ C$. | 132 |
| Figure 6.4: | Normalised XRD patterns of SAO, SAO(2.5), SAO(5), SAO(10), SAO(15) and SAO(20) composites calcined at $700^\circ C$. | 134 |
| Figure 6.5: | Normalised XRD patterns of SAO, SAO(2.5), SAO(5), SAO(10), SAO(15) and SAO(20) composites calcined at $1200^\circ C$. | 134 |
| Figure 6.6: | Normalised XRD patterns of SAO(20) nanocomposites calcined at different temperatures. | 135 |

| | | |
|---------------------|---|-----|
| Figure 6.7: | The fitted experimental data of XRD using Fullprof program with $P6_3mc$ and $P6_322$, and $P6_3mc$ and $P2_1$, for 800 °C and 1000 °C calcined SAO(20) nanocomposites, respectively. | 136 |
| Figure 6.8: | The integral peak area ratio of the MP peak (211) to the main peak (-220) or (102) of MP or HP respectively in the XRD patterns of (a) ZnO-SAO composite with varying ZnO concentration and calcined at 700 °C and (b) SAO(20) composite with increasing calcination temperature. | 137 |
| Figure 6.9: | The XPS spectra of (a) SAO(2.5) and SAO(20) composites calcined at 700 °C and the SAO(20) composite calcined at 1200 °C in full scan, (b) O 1s core level spectra deconvoluted into three peaks, (c) Zn 2p core level spectra for SAO(2.5) and SAO(20) calcined at 700 °C and SAO (20) calcined at 1200 °C and (d) a typical Al 2p spectrum of SAO(20) composite calcined at 1200 °C after deconvolution. | 140 |
| Figure 6.10: | Photoluminescence spectra obtained by using $E_x=266$ nm for SAO(ZnO%) composites calcined at different temperatures in the range of 700-1200 °C. | 142 |
| Figure 6.11: | Photoluminescence spectra obtained by using $E_x=266$ nm for SAO(20) composites calcined at different temperatures in the range of 700-1200 °C. | 143 |
| Figure 6.12: | The deconvoluted spectra of SAO(20) composites calcined at (a) 700 °C and (b) 1200 °C. | 144 |
| Figure 6.13: | CIE chromaticity diagram of ZnO and SAO(20) composites calcined at different temperature. | 144 |
| Figure 6.14: | Photoluminescence spectra obtained by using $E_x=355$ nm for SAO(20) composites calcined at 1200 °C along with the excitation spectra for emission at 550, 600 and 655nm. | 145 |
| Figure 6.15: | The proposed energy band diagram of the electron transfer in ZnO-SAO composites after excitation. | 147 |
| Figure 6.16: | Thermoluminescence spectra of SAO(20) composite calcined at 700 °C and 1200 °C, before (a and c) and after (b and d) γ irradiation. | 149 |

- Figure 6.17:** Calculation of activation energy E of traps for SAO(20) composite calcined at 700 °C with respect to the TL glow peak at ~323 °C. 151
- Figure 6.18:** Calculation of the activation energy E of traps for SAO(20) composite calcined at 1200 °C with respect to the TL glow peak at ~323 °C and glow peak at ~158 °C. 151
- Figure 6.19:** The linear response of integrated thermoluminescence of SAO(20) composite calcined at 1200 °C as a function of the γ irradiation dose with respect to the TL glow peak at ~158 °C. 152