

# Contents

## Table of contents

## List of Publications

## List of Figures

## List of Tables

<b>Chapter 1</b>	<b>Introduction</b>	1-17
1.1	Background and motivation	1
1.2	The electroactive response of natural bone	2
1.3.	Overview of piezoelectric bioceramics	5
1.4	Surface polarization and external electrical stimulation induced cellular response	6
1.5	Surface charge induced antibacterial response	7
1.6	Objectives	8
1.7	Outlines for the thesis	8
<b>Chapter 2</b>	<b>Literature Review</b>	18-102
2.1	Introduction	18
2.2	Piezoelectric biomaterials	25
2.3	Processing-related challenges for piezoelectric NKN-based ceramics system	30
2.4	Addressing the processing concerns for piezoelectric NKN-based ceramics	35
2.4.1	Conventional processing routes	37
2.4.2	Advanced processing routes	38
2.4.3	Chemical modification	42
2.5	Piezoelectricity and biocompatibility	46

2.5.1	Origin of biomineralization and cytocompatibility	46
2.5.2	Origin of bone healing	50
2.5.3	Influence of electrical stimulation on the biological response	53
2.5.4	Biomaterials-based perspective	54
2.5.4.1	NKN-based piezoelectric ceramics	54
2.5.4.2	Other piezoelectric ceramics	56
2.5.4.3	Piezoelectric polymers	60
<b>2.6</b>	<b>Surface charge polarization induced antibacterial response</b>	<b>62</b>
2.6.1	Bacterial infection	62
2.6.2	Influence of surface charge and other external stimuli on bacteria	62
<b>Chapter 3</b>	<b>Experimental Design (Materials and methods)</b>	<b>103-130</b>
<b>3.1</b>	<b>Synthesis</b>	<b>103</b>
3.1.1	Synthesis of sodium potassium niobates [ $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$ ( $x = 0.2 - 0.8$ ), NKN]	103
3.1.2	Synthesis of hydroxyapatite (HA)	104
<b>3.2</b>	<b>Consolidation of synthesized <math>\text{Na}_x\text{K}_{(1-x)}\text{NbO}_3</math> and HA powders</b>	<b>105</b>
<b>3.3</b>	<b>Characterization</b>	<b>106</b>
3.3.1	X-ray diffraction analyses	106
3.3.2	Fourier transform infrared (FTIR) spectroscopy	108
3.3.3	Microstructural analyses	108
<b>3.4</b>	<b>Densification and mechanical property measurement</b>	<b>108</b>
<b>3.5</b>	<b>Ion leaching study of NKN samples in simulated body fluid (SBF)</b>	<b>109</b>

<b>3.6</b>	<b>Polarization treatment of the samples</b>	109
<b>3.7</b>	<b>Surface charge measurement</b>	110
<b>3.8</b>	<b>X-ray photoelectron spectroscopy (XPS)</b>	111
<b>3.9</b>	<b>Physical characterization (Contact angle measurement)</b>	111
<b>3.10</b>	<b>Cellular response</b>	111
3.10.1	Quantitative analyses	112
3.10.1.1	MTT assay	112
3.10.1.2	Alkaline phosphatase (ALP) activity	113
3.10.2	Morphological analyses of adhered cells	114
3.10.3	Intracellular Ca <sup>2+</sup> ions measurement	114
<b>3.11</b>	<b>Antibacterial response</b>	116
3.11.1	Quantitative analyses	116
3.11.1.1	MTT assay	116
3.11.2	Qualitative analyses	117
3.11.2.1	Fluorescence imaging	117
3.11.2.2	Disk diffusion method	117
<b>3.12</b>	<b><i>In vivo</i> assessment of systematic toxicity of nano-sized NKN powder</b>	118
3.12.1	Nano-sized powder preparation	118
3.12.2	Characterization of nano-powders	119
3.12.3	Preparation of eluate solution	119
3.12.4	Cell - NKN nanoparticles interaction	119
3.12.5	Animal study	121
3.12.5.1	General observation	122
3.12.5.2	Biochemical assay for serum assessment	123
3.12.5.3	Inflammatory test with organs	124

3.12.5.3.1	Inflammatory cytokines profiling	124
3.12.5.3.2	Histopathological analyses	125
3.12.6	Statistical analyses	125
<b>Chapter 4</b>	<b>Combined effect of surface polarization and external electrical stimulation towards accelerated osteogenic response of <math>\text{Na}_x\text{K}_{1-x}\text{NbO}_3</math> (<math>x = 0.2 - 0.8</math>) piezobioceramics</b>	131-172
<b>4.1</b>	<b>Phase evolution</b>	132
4.1.1	XRD analyses	132
4.1.2	Crystallite size and strain measurement	135
4.1.3	Fourier transform infrared (FTIR) spectroscopy	138
<b>4.2</b>	<b>Microstructural analysis</b>	139
<b>4.3</b>	<b>The densification and mechanical property (Vicker's Hardness) measurement</b>	141
<b>4.4</b>	<b>Leaching behavior of NKN pellets in biological fluid (SBF)</b>	142
<b>4.5</b>	<b>Charge measurement</b>	143
<b>4.6</b>	<b>X-ray photoelectron spectroscopy (XPS) analyses</b>	144
<b>4.7</b>	<b>Contact angle measurement</b>	147
<b>4.8</b>	<b>Cellular response</b>	148
4.8.1	Polarization induced early-stage cell adhesion	148
4.8.2	Combined effect of surface polarization and dynamic electrical stimulation	151
4.8.2.1	MTT assay	151
4.8.2.2	Alkaline phosphatase (ALP) activity assessment	155
4.8.2.3	Morphological analyses of adhered cells	158
4.8.2.4	Intracellular $\text{Ca}^{2+}$ measurement	160
<b>4.9</b>	<b>Discussion</b>	162

<b>Chapter 5</b>	<b>Antibacterial response of surface polarized and compositionally modified biocompatible <math>\text{Na}_x\text{K}_{1-x}\text{NbO}_3</math> (<math>x = 0.2 - 0.8</math>) ceramics</b>	173-200
<b>5.1</b>	<b>Quantitative antibacterial analyses or MTT assay</b>	173
<b>5.2</b>	<b>Qualitative analyses</b>	178
5.2.1	Live/ dead assay	178
5.2.2	Disk diffusion method of colony counting	179
<b>5.3</b>	<b>Enzymatic activity for reactive oxygen species (ROS) measurement</b>	182
5.3.1	SOD assay	182
5.3.2	Catalase assay	185
5.3.3	ROS induced damaged protein estimation	187
5.3.4	LPO assay	189
<b>Chapter 6</b>	<b>An <i>in vivo</i> toxicity assessment of piezoelectric <math>\text{Na}_x\text{K}_{1-x}\text{NbO}_3</math> (<math>x = 0.2 - 0.8</math>) nanoparticulates towards bone tissue engineering approach</b>	201-236
<b>6.1</b>	<b>Characterization of <math>\text{Na}_x\text{K}_{1-x}\text{NbO}_3</math> nanoparticulates</b>	201
<b>6.2</b>	<b>Morphological analyses</b>	202
<b>6.3</b>	<b>Initial screening of toxicity (Cell culture study)</b>	203
<b>6.4</b>	<b>Animal study</b>	206
6.4.1	General observations	206
6.4.2	Effect of intra-articular injection of N1, N2 and N3 compositions on the body weight	207
6.4.3	Biochemical assay	208
6.4.4	Inflammatory cytokines analyses	210
6.4.5	Histopathological analyses (hematoxylin and eosin staining)	212
<b>Chapter 7</b>	<b>Conclusion and scope for the future work</b>	237-241
	<b>Conclusions</b>	237
	<b>Future scope</b>	240



## List of figures

- Fig. 2.1 : Stress generated electrical charges in natural bone and piezoelectric biomaterials induced endogenous cellular potential and bone formation. (A) Schematic demonstration of the generation of aligned dipoles or surface charge on piezoelectric ceramic ( $\text{BaTiO}_3$ ) and polymer (PLLA) with the application of mechanical stress, similar to human bone. (B) Stress generated surface electrical charge on the circumference of human femur. (C) Schematic illustration of the generation of surface electrical charge on strained piezoelectric material and resulting hyper-polarization/ depolarization of cellular membrane. (D) Schematic representation of built-in electric field between positively charged nanocomposite and negatively charged bone wall, which enhances the osseointegration. (E) Histological evidences demonstrating significant neobone formation on the positively charged implant, when compared to negatively charged and uncharged implant (Yellow dotted block: implant-tissue interface, NB: nascent bone, FT: fibrous tissue, BFO:  $\text{BiFeO}_3$ , STO:  $\text{SrTiO}_3$ ). 21
- Fig. 2.2 : Piezoelectric potential generated from natural bone during regular physiological activity. [(A), (B) and (C)] PVDF based piezoelectric sensors (PS) as detectors of human activity in terms of piezoelectricity induced voltage output. [D] P(VDF-TrFE) based piezo-polymers (nanogenerator) implanted in the thigh of Sprague Dawley rat, mimicking piezoelectric potential generation during the regular activity. (A) PS nanocomposite, fabricated with PVDF/  $\text{SiO}_2$  coated NiO assembled with gloves to determine the piezoelectric voltage output variation during stretching and bending movement of index, middle and ring fingers. (B) A PS nanocomposite with tetrapod ZnO/ PVDF/ polyester fabric, attached with elbow, to evaluate the amount of voltage output during bending and release. (C) A PS fabricated with PVDF/ graphene in polyester fabric attached with marked region to determine the voltage output variation during running. (D) Electrospun P(VDF-TrFE) nanoscaffold implanted in the thigh of Sprague Dawley rat. The leg of rat was pulled up and released through a motor (bottom-right) and resulting variation in current output are shown (top-right) during pulling and releasing. The current and voltage output are also shown in bottom-left and bottom-middle graph, respectively in the pulling condition of rat's leg. 23
- Fig. 2.3 : Schematic illustrating the temperature dependent phase transformations (a) In  $\text{Na}_{0.5}\text{K}_{0.5}\text{NbO}_3$  and (b) In  $\text{BaTiO}_3$  ceramics. 25

- Fig. 2.4 : Classification of various crystal classes on the basis of the center of symmetry with reference to piezoelectricity, pyroelectricity and ferroelectricity. 29
- Fig. 2.5 : (a). Phase diagram of  $\text{KNbO}_3\text{-NaNbO}_3$  solid solution, where P and F denote the paraelectric and ferroelectric phases, respectively. R, O, T and C indicate rhombohedral, monoclinic / orthorhombic, tetragonal and cubic phases, respectively. In  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$ , the morphotropic phase boundary (MPB) at  $x = 0.5$  distinguishes two orthorhombic and two tetragonal phases. Below Curie temperature, polymorphs like tetragonal - monoclinic / orthorhombic and monoclinic / orthorhombic - rhombohedral coexist at about  $200^\circ\text{C}$  and  $-160^\circ\text{C}$ , respectively. (b) Polymorphic phase transformation (PPT): tetragonal to monoclinic / orthorhombic (polymorphs) phase transformation temperature of NKN can be shifted to room temperature by chemical modification, indicating the dependency of PPT on composition as well as temperature, (c) Morphotropic phase boundary (MPB): Coexistence of rhombohedral and tetragonal phases at a certain composition. 32
- Fig. 2.6 : Schematic representing key issues, associated with the processing of stoichiometric NKN 35
- Fig. 2.7 : Surface polarization induced bioactivity and cellular response, in vitro and in vitro. Polarized surfaces of piezoelectric materials promote the adsorption of apatite ions ( $\text{Ca}^{2+}$ ,  $\text{HPO}_4^{2-}$ ) or proteins and cell adhesion, which consequently influence the hard tissue regeneration. 48
- Fig. 2.8 : Schematic illustration of the effect of mechanical stimulation on cell metabolism through intracellular electrical signal transduction, leading to activation of mechanoreceptors. Electromechanical signals facilitate outside-in  $\text{Ca}^{2+}$  ions influx through the opening of voltage gated  $\text{Ca}^{2+}$  channels (VGCC) and stretch activated calcium channels (SACC). Consequently, intracellular ions increase which activate the calmodulated protein and calcineurin. These calcium activated calcineurin dephosphorylates the phosphorylated nuclear factor of activated cells (NF-AT) and shifts towards the nucleus, where it executes gene transcription. Mechanically stimulated membrane receptors open up receptor channels and permit intracellular  $\text{Ca}^{++}$  ions from endoplasmic reticulum calcium stores. Also, physiological loads directly activate mechanoreceptors of the cell membrane like integrin, which actuate PKC (protein kinase C) and MAPK (mitogen activated protein kinase) signaling pathways. These signaling cascade propagates towards the nucleus, where it interacts with 51



	<i>mechanosensitive transcription factor and results in gene transcription.</i>	
Fig. 2.9	: <i>Intra-articularly injected HA-40 wt.% BaTiO<sub>3</sub> particulate in the knee joint of mice could not cause any systematic toxicity in vital organs, such as heart, kidney, liver and lung at 7 days of post-injection, as evident from representative fluorescent images.</i>	57
Fig. 3.1	: <i>Flow chart for the synthesis of Na<sub>x</sub>K<sub>(1-x)</sub>NbO<sub>3</sub> (x = 0.2, 0.5 and 0.8).</i>	104
Fig. 3.2	: <i>Digital images of (a) Conventional press, (b) Green pellets, (c) Cold isostatic press.</i>	105
Fig. 3.3	: <i>Surface charge polarization and measurement of thermally stimulated depolarized current. (a) Schematic illustration of high voltage (25 kV) corona poling unit for the development of electrical charges on the surface of the specimen. (b) Schematic shows the thermally stimulated depolarized current measurement setup includes picoammeter, furnace and simulator.</i>	110
Fig. 3.4	: <i>Schematic demonstrating the synergistic action of surface charge polarization and external electrical stimulation during cell culture experiment. The application of dynamic electrical stimulation (1 V/cm, 400 μs), while cells are being adhered on the (c) Neg. Pol. (d) Pos. Pol. surfaces.</i>	112
Fig. 3.5	: <i>Demonstration of intra-articular injection of NKN nanoparticles in the knee (synovial) joint of Wistar rat.</i>	122
Fig. 3.6	: <i>Schematic illustration of in vivo studies performed after intra-articular injection of Na<sub>x</sub>K<sub>1-x</sub>NbO<sub>3</sub> nanoparticles for 7 days. The histological analysis was done for the heart, liver, kidney, spleen and knee joint to for the inspection of microscopic changes in such organs. The inflammatory cytokines were examined on liver and spleen tissues to observe the level of inflammation after particulate injection. The blood serum extracted from the rats was used for biochemical assays (ALP and Creatinine) to analyze the cellular metabolism.</i>	123
Fig. 4.1	: <i>XRD patterns of the sintered HA and Na<sub>x</sub>K<sub>1-x</sub>NbO<sub>3</sub> (x = 0.2, 0.5 and 0.8) samples, (b) Positions of the most intense diffraction peaks (2 θ<sub>M</sub>) in Na<sub>x</sub>K<sub>1-x</sub>NbO<sub>3</sub> (x = 0.2, 0.5 and 0.8).</i>	133
Fig. 4.2	: <i>Rietveld refinement analyses for NKN samples. The combined X-ray diffraction spectra for sintered Na<sub>x</sub>K<sub>1-x</sub>NbO<sub>3</sub> (x = 0.2 - 0.8) samples. Enlarged view demonstrating the observed and</i>	134

refined data for  $x = 0.2, 0.5$  and  $0.8$  are illustrated.

- Fig. 4.3 : 4.3. X-ray peak profile analyses for  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) samples. Representation of plots obtained from (a) Modified Scherrer, (b) Williamson-Hall, and (c) Size-strain methods for  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  samples. 138
- Fig. 4.4 : FTIR spectra of the sintered HA and  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5$  and  $0.8$ ) samples. 139
- Fig. 4.5 : Scanning electron microscopy (SEM) images and EDS graphs for  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  powders, (a)  $x = 0.2$ , (b)  $x = 0.5$ , (c)  $x = 0.8$ , calcined at  $900^\circ\text{C}$  for 10 h. 140
- Fig. 4.6 : Scanning electron microscopy (SEM) images and EDS graphs for fractured  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  samples, (a)  $x = 0.2$ , (b)  $x = 0.5$ , (c)  $x = 0.8$ , sintered at  $1010, 1075$  and  $1120^\circ\text{C}$ , respectively. 140
- Fig. 4.7 : Mechanical properties of  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) and HA samples. Hardness and compressive strength of sintered specimens of  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  and HA. 142
- Fig. 4.8 :  $\text{Na}^+$  and  $\text{K}^+$  leaching profiles from  $\text{Na}_{0.2}\text{K}_{0.8}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) in SBF. The plot represents the dynamic changes in concentrations of  $\text{Na}^+$  and  $\text{K}^+$ , after immersion of  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  samples in SBF. 143
- Fig. 4.9 : Thermally stimulated depolarization current (TSDC) measurement. TSDC spectra of for  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) ceramics, polarized at  $25\text{ kV}$ , followed by depolarization at the heating rate of  $5^\circ\text{C}/\text{min}$ . upto  $500^\circ\text{C}$ . 144
- Fig. 4.10 : XPS spectra for non-Pol. and polarized surfaces of NKN. (a) XPS survey spectrum of non-Pol. and polarized NKN for Na ( $1s$ ), K ( $2p$ ), Nb ( $3p$ ), Nb ( $3d$ ), C ( $1s$ ) and O ( $1s$ ) orbitals states. (b) and (c) represent the O  $1s$  XPS spectra for non-Pol. and polarized NKN samples, respectively. 146
- Fig. 4.11 : Influence of surface polarization charge on hydrophilicity. The contact angle ( $^\circ$ ) values for non-Pol. and polarized surfaces of  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) and HA in (a) DI water and (b) DMEM media. 148
- Fig. 4.12 : Influence of polarization on early-stage adhesion (after 6h) of MG-63 cells. (a) The representative florescence images of MG-63 cells, adhered on non-Pol. and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  and control samples. (b) The plot, representing the projected area of the adhered cells ( $n = 20$ ), on the non-Pol. and polarized NKN and control samples. 150

- Fig. 4.13 : Quantitative cellular response on non-treated and treated NKN and control samples. The plots representing the quantitative cellular response, using (a) MG-63 cells and (b) hMSCs, on non-Pol. and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) and control samples in presence and absence of dynamic pulsed electrical stimulation. 154
- Fig. 4.14 : Osteogenic differentiation response of non-treated and treated piezoelectric NKN and control samples. The plot illustrating the alkaline phosphatase (ALP) activity on the non-Pol., electrostatically (Pos. and Neg. Pol.) – electrically stimulated (dynamic) Pos. Pol. (E. S. Pos.) and electrically stimulated (dynamic) Neg. Pol. (E. S. Neg.)  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) and HA samples, after (a) 7 and (b) 14 days. 157
- Fig. 4.15 : Morphological analyses of adhered cells on non-treated and treated NKN and control samples. (a) Representative fluorescence microscopic images of stained hMSCs, adhered on the non-treated and treated (Electrostatically/dynamically stimulated) piezoelectric  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  samples and control. 159
- Fig. 4.16 : The level of intracellular  $\text{Ca}^{2+}$  on non-treated and treated NKN and control samples, cultured with MG-63 cells. The plot representing the mean of the peak values of the ratio of fluorescence intensity at 340 and 380 nm, measured for the cells loaded with intracellular  $\text{Ca}^{2+}$  indicator Fura-2 AM on the non-treated and treated (Electrostatically/dynamically stimulated) piezoelectric  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  samples and control. 161
- Fig. 4.17 : Schematic demonstrating the synergized effect of Neg. Pol. surface and dynamic pulsed electrical stimulation in promoting cellular response of piezoelectric NKN. 164
- Fig. 5.1 : Quantitative analyses of antibacterial response on the non-polarized and polarized surfaces of  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) and HA samples for (a) *S. aureus* and (b) *E. coli* bacteria. 175
- Fig. 5.2 : Antibacterial ratio % (calculated from eqn. 3.5, chapter 3) for the non-polarized and polarized surfaces of  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) and HA samples with (a) *S. aureus* and (b) *E. coli* bacteria. 177
- Fig. 5.3 : Florescence microscopy images representing the live and dead strain of (a) *S. aureus* and (b) *E. coli* bacteria, exposed on non-polarized and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) and HA samples after 10 h of incubation in growth medium. Live and dead bacteria are strained green and red, respectively. Scale bar = 25  $\mu\text{m}$ . 178

- Fig. 5.4 : Digital camera images of (A) *S. aureus* and (C) *E. coli* bacterial colonies on agar plate exposed with non-polarized and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) and HA samples. 181
- Fig. 5.5 : The plots illustrating the concentration of superoxide ( $\bullet\text{O}_2^-$ ) on non-polarized and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) as well as HA samples for (a) *S. aureus* and (b) *E. coli* bacteria. 184
- Fig. 5.6 : The plots representing the catalase activity/ seconds on non-polarized and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) as well as HA samples for (a) *S. aureus* and (b) *E. coli* bacteria. 186
- Fig. 5.7 : The plots representing the leaked amount ( $n$  mol/ mg), of intracellular bacterial protein for (a) *S. aureus* and (b) *E. coli* bacteria on non-polarized and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) and HA samples. 189
- Fig. 5.8 : The plots representing the MDA concentration (nmol./mg) (calculated from eqn. 5.2) for (a) *S. aureus* and (b) *E. coli* bacteria, cultured on non-polarized and polarized  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) and HA samples. 192
- Fig. 5.9 : Schematic representing various mechanisms of antibacterial response of NKN samples, induced by surface charge polarization 195
- Fig. 6.1 : X-ray diffraction pattern of micro-sized and nano-sized (after 10 h planetary ball milling)  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2 - 0.8$ ) powders. Enlarged view illustrating the position and intensity of most intense diffraction peaks of NKN samples before and after ball milling. (B. M: Planetary ball milling). 201
- Fig. 6.2 : High resolution scanning electron microscopy (HRSEM) images and EDS graphs for  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  nano-powders, (a)  $x = 0.2$ , (b) 0.5, (c) 0.8, planetary ball milled for 10 h. 203
- Fig. 6.3 : (A) Qualitative and (B) quantitative response of MG-63 cells after 24 and 72 h of culture on  $\text{Na}_x\text{K}_{1-x}\text{NbO}_3$  ( $x = 0.2, 0.5, 0.8$ ) nanopowders i.e., N1, N2, N3 of concentrations, C1 (0.25 mg/ml), C2 (2.5 mg/ml) and C3 (25 mg/ml). Scale bar = 100  $\mu\text{m}$ . 205
- Fig. 6.4 : Representation of the paws of the rats before and 7<sup>th</sup> days' post intra-articular injection of NKN nanoparticulates and the knee joint, confirming the absence of any inflammation. 207
- Fig. 6.5 : Effect of intra-articular injection of N1, N2, and N3 compounds on body weight of the rats during the experimental protocol. All values are represented as mean  $\pm$  SD ( $n = 6$  rats/group) (Two- 208

way ANOVA followed by Bonferroni post hoc test).

- Fig. 6.6      *Effect of intra-articular injection of N1, N2, and N3 compounds on serum concentration of (a) Alkaline phosphatase activity (ALP) and (b) Creatinine, at the end of day 7 of the experimental protocol.*      210
- Fig. 6.7      : *The plots representing the percentage of fold change (w. r. t. GAPDH) in gene expression of proinflammatory (TNF- $\alpha$  and IL-12) and anti-inflammatory (IL-4 and IL-10) cytokines for N1, N2, N3 treated, saline treated and control (non-injected) rats in (a) liver and (b) spleen.*      212
- Fig. 6.8      : *Histopathological images of hematoxylin and eosin (H & E) stained heart tissues of (a) Control (non-injected), (b) Saline, (c) N1, (d) N2 and (e) N3 nanoparticulate eluates treated groups of rats after 7 days of intra-articular injection.*      214
- Fig. 6.9      : *Histopathological images of H & E stained liver tissues of (a) Control (non-injected), (b) Saline, (c) N1, (d) N2 and (e) N3 nanoparticulate eluates treated groups of rats after 7 days of intra-articular injection.*      216
- Fig. 6.10 :      *Histopathological images of H & E stained kidney tissues of (a) Control (non-injected), (b) Saline, (c) N1, (d) N2 and (e) N3 nanoparticulate eluates treated groups of rats after 7 days of intra-articular injection.*      218
- Fig. 6.11:      *Histopathological images of H & E stained spleen tissues of (a) Control (non-injected), (b) Saline, (c) N1, (d) N2 and (e) N3 nanoparticulate eluates treated groups of rats after 7 days of intra-articular injection.*      220
- Fig. 6.12 :      *Histopathological images of H & E stained knee joint tissues of (a) Control (non-injected), (b) Saline, (c) N1, (d) N2 and (e) N3 nanoparticulate eluates treated groups of rats after 7 days of intra-articular injection. NKN treated knee joint tissues are showing smooth cartilage with the deposition of particles.*      223

## List of Tables

Table 2.1	<i>A comparison of dielectric constants (<math>\epsilon_r</math>), piezoelectric strain coefficients (<math>d_{33}</math>), mechanical quality factors (<math>Q_m</math>), remnant polarization (<math>P_r</math>), electromechanical coupling coefficients (<math>k_p</math>) and pyroelectric coefficients (<math>p</math>) of various piezoelectric biomaterials with those of the natural bone.</i>	26
Table 2.2	<i>Table 2.2. Effect of various processing techniques on densification (<math>\% \rho_{th}</math>), piezoelectric strain coefficient (<math>d_{33}</math>) and electromechanical coupling coefficient (<math>k_p</math>) of the NKN/ NKN-based ceramics.</i>	41
Table 2.3	<i>Table 2.3. Effect of doping on densification, piezoelectric (<math>d_{33}</math>) and dielectric (<math>\epsilon_r</math>) properties of NKN.</i>	45
Table 3.1	<i>Sintering parameters, optimized for the developed compositions.</i>	106
Table 4.1	<i>Table 4.1. The refined unit cell parameters and the positions of most intense diffraction peak (<math>2\theta_M</math>) for the <math>Na_xK_{1-x}NbO_3</math> (<math>x = 0.2, 0.5</math> and <math>0.8</math>) samples.</i>	133
Table 4.2	<i>The final obtained values of various refined parameters, corresponding to monoclinic phases in <math>Na_xK_{1-x}NbO_3</math> (<math>x = 0.2, 0.5, 0.8</math>) samples, sintered at 1010, 1075 and 1120 °C, respectively.</i>	135
Table 4.3	<i>Geometrical parameters of solid state synthesized <math>Na_xK_{1-x}NbO_3</math> (<math>x = 0.2, 0.5, 0.8</math>) samples, sintered at 1010, 1075 and 1120 °C, respectively.</i>	137