
PREFACE

Permanent magnets are a significant component in various applications like motor, wind turbine, generator, computer device, medical equipment, and many more. There is a huge demand for permanent magnets which was valued at \$17.85 Billion globally in 2018 and are expected to reach \$34.7 Billion by 2026. Among these magnets, NdFeB is the best performing magnet presently available in the market due to their high energy product. However, the market restriction and supply issues of rare-earth elements (REEs) due to the monopoly of China and the negative environmental effects of REEs extraction are demanding less dependency on REEs. It brings the challenge of developing a rare-earth free permanent magnet with high energy density.

Strontium hexaferrite (SrM) magnets represent the largest magnet group being used nowadays by volume. SrM is a ferrimagnetic material whose magnetic properties are inherently linked to the crystal structure and grain morphology. Though, it has a small energy density which is required to improve to reduce the dependency on NdFeB. Energy density is a key figure of merit, which is required to be high for better performance and is linked with the saturation magnetization (M_s) and coercivity (H_c) of the magnetic material. Due to high magnetocrystalline anisotropy, decent magnetism, chemical inertness, and high Curie temperature, these magnets are continuously drawing the attention of research communities to improve the low energy density of SrM with different means. It is found as the most faithful base magnet in terms of abundance and economic balance, which requires more or less reformation and advancement in the aspect of magnetic properties. Improvement in M_s and H_c of SrM magnet, even mildly, could open up the possibilities of large-scale immersion of strontium hexaferrite based magnets in numerous permanent

magnet applications. In the past several years, enormous improvement has been made toward enhancing the magnetic properties of SrM.

The thesis work is focused on the ‘development of rare-earth free permanent magnets with improved magnetic properties’, where the magnetic properties of strontium hexaferrites have been tried to improve toward the proposed objective. Detailed investigations on the structural, magnetic, and dielectric properties of five different SrM-based compositions (not reported earlier by other authors) have indicated a good improvement in SrM compositions. The results of different SrM-based series are briefly outlined here. It is arranged into nine chapters, and a brief description of each chapter is as follows:

Chapter 1 provides a brief introduction to permanent magnets and the different magnetic properties of a magnetic material. The featured characteristics of strontium hexaferrite magnets are discussed with the requirement of certain criteria that must be fulfilled for developing a permanent magnet. Concerning the significance of these criteria, literature surveys on the effect of synthesis techniques and current progress in magnetic properties of strontium hexaferrite magnets due to the substitution of various non-rare-earth elements are summarized in this chapter. Finally, it is concluded with the scope and objective of the present work.

Chapter 2 provides a detailed overview of the experimental techniques applied in the present thesis work. It includes sample preparation procedures and a detailed introduction to the working principles of different characterizing instruments that are used in the different studies of synthesized samples.

Chapter 3 presents the synthesis of a $\text{SrFe}_{12-x-y}\text{Co}_x\text{Cr}_y\text{O}_{19}$ ($0 \leq x, y \leq 1$) hexaferrite. The effect of Co-Cr substitution on the structural, magnetic, and dielectric properties of SrM is studied. XRD pattern confirms the formation of magnetoplumbite hexagonal

structure of SrM hexaferrite. Co ion substitution is found favorable to improve the M_s value with a drastic decrease in H_c , resulting in a soft magnetic behavior of samples. In contrast, Cr substitution is observed to significantly enhance the H_c value (almost double) without adversely affecting the M_s , resulting in a better hard magnetic behavior of strontium hexaferrite. Also, both these elements are found liable for improving the ac-resistivity of pristine strontium hexaferrite.

Chapter 4 presents the synthesis of a $\text{Sr}_{1-x}\text{Cr}_x\text{Fe}_{12-y}\text{Zn}_y\text{O}_{19}$ ($0 \leq x \leq 0.8$; $0 \leq y \leq 1$) hexaferrite. The effect of Cr-Zn substitution on the structural, magnetic, and dielectric properties of SrM is studied. XRD pattern confirms the formation of magnetoplumbite hexagonal structure of SrM hexaferrite. Cr substitution at Sr site is also found favorable to improve the H_c value but not as significant as observed at Fe site, with a slight decline in M_s value. Zn substitution at Fe site of SrM is observed to improve M_s value considerably with a drastic reduction in H_c value, resulting in a soft magnetic behavior of the sample. Despite the sharp H_c dilution due to Zn ion, Cr substitution retained the hard magnetic characteristic of samples by maintaining H_c value greater than at least 1 kOe. Also, both these elements are found liable for improving the ac-resistivity of pristine strontium hexaferrite.

Chapter 5 presents the synthesis of a $\text{SrFe}_{12-x-y}\text{Ni}_x\text{Al}_y\text{O}_{19}$ ($0.005 \leq x \leq 0.02$; $1 \leq y \leq 4$) hexaferrite. The effect of Ni-Al substitution on the structural, magnetic, and dielectric properties of SrM is studied. XRD pattern confirms the formation of magnetoplumbite hexagonal structure of SrM hexaferrite. Ni substitution is found favorable to improve the M_s value of samples without adversely affecting the H_c . Al substitution is observed to significantly increase the H_c value of SrM, even higher than NdFeB but at the cost of M_s value. Also, both these elements are found liable for improving the ac-resistivity of pristine strontium hexaferrite.

Chapter 6 presents the synthesis of a $\text{SrFe}_8\text{Al}_4\text{O}_{19-x}\text{Bi}_2\text{O}_3$ ($0 \leq x \leq 5$ wt%), where the doping effect of Bi_2O_3 sintering aid and the effect of different sintering temperature is studied on the structural, magnetic, and dielectric properties of Al-substituted SrM. XRD pattern confirms the formation of magnetoplumbite hexagonal structure of SrM hexaferrite. Mainly, the study of this chapter is motivated to compensate for the M_s loss in $\text{SrFe}_8\text{Al}_4\text{O}_{19}$ (a drawback of 4 Al substitution in SrM). The doping concentration of Bi_2O_3 and sintering temperature is optimized to realize better magnetic properties in $\text{SrFe}_8\text{Al}_4\text{O}_{19}$. Both Bi_2O_3 dopings and T_{sin} variation have reduced the ac-resistivity of samples compared to pristine strontium hexaferrite, but it is still higher than NdFeB.

Chapter 7 presents the synthesis of a $\text{SrFe}_{8-x}\text{Al}_4\text{Zn}_x\text{O}_{19}$ ($0 \leq x \leq 1$) hexaferrite. The effect of Al-Zn substitution on the structural, magnetic, and dielectric properties of SrM is studied. XRD pattern confirms the formation of magnetoplumbite hexagonal structure of SrM hexaferrite. Al substitution is observed to considerably increase the H_c value, even higher than NdFeB, but at the cost of M_s value. Zn substitution is found more prominent in improving the M_s of compositions but at little expense of H_c . An improvement in both M_s and H_c values is observed for small Zn substitution ($x = 0.2$). Zn substitution improves the ac-resistivity of Al-substituted SrM, but it is less than pristine strontium hexaferrite (still higher than NdFeB).

Chapter 8 presents the progress in energy density of the three best compositions of different series concerning the improvement in magnetic properties of strontium hexaferrite in comparison to the NdFeB. Three compositions from different series of the thesis work is selected here to demonstrate the enhancement in $(BH)_{\text{max}}$, due to their high H_c , either nearly approaching to the H_c of NdFeB (~ 15.07 kOe) or even higher than that. Also, Curie temperature analysis of these samples is given in this chapter to deliberate the operating temperature efficiency of synthesized permanent magnets.

Chapter 9 briefly summarizes the important findings of the thesis work. A decent improvement in magnetic properties of strontium hexaferrite magnets is deliberated here with the optimal amount of substituted element and optimization in synthesis factors. It also highlights the future scope of research on this material.

