

# **Semiconducting Nanoparticles/PVDF Nanocomposites with High Dielectric strength for Capacitive Energy Storage**



**Thesis Submitted in Partial Fulfillment for the  
Award of Degree**

**Doctor of Philosophy**

By

*Vishwa Pratap Singh*

**SCHOOL OF MATERIALS SCIENCE & TECHNOLOGY  
INDIAN INSTITUTE OF TECHNOLOGY  
(BANARAS HINDU UNIVERSITY)  
VARANASI – 221005  
INDIA**

**Roll No. 17031505**

**2022**



*Dedicated*  
*To*  
*My Family and*  
*mentors*



## CERTIFICATE

It is certified that the work contained in the thesis titled "*Semiconducting Nanoparticles/PVDF Nanocomposites with High Dielectric Strength for Capacitive Energy Storage*" by "*Vishwa Pratap Singh*" has been carried out under my supervision and that this work has not been submitted elsewhere for a degree.

It is further certified that the student has fulfilled all the requirements of Comprehensive, Candidacy and SOTA for the award of Ph.D. degree.

Date...31/12/2022

Place: Varanasi

(Dr. Akhilesh Kumar Singh)

Supervisor

Associate Professor

School of Materials Science & Technology

IIT (BHU), Varanasi

Associate Professor/सह-आचार्य

School of Materials Science & Technology/पदार्थ विज्ञान एवं प्रौद्योगिकी स्कूल  
Indian Institute of Technology/भारतीय प्रौद्योगिकी संस्थान  
(Banaras Hindu University), Varanasi/काशी हिन्दू विश्वविद्यालय, वाराणसी



## DECLARATION BY THE CANDIDATE

I, **Vishwa Pratap Singh**, certify that the work embodied in this Ph.D. thesis is my own bonafide work carried out by me under the supervision of **Dr. Akhilesh Kumar Singh** for a period from **December 2017** to **December 2022** at the **School of Materials Science and Technology**, Indian Institute of Technology (Banaras Hindu University), Varanasi. The matter embodied in this Ph.D. thesis has not been submitted for the award of any other degree/diploma. I declare that I have faithfully acknowledged and given credits to the research workers wherever their works have been cited in my work in this thesis. I further declare that I have not wilfully copied any other's work, paragraphs, text, data, results, *etc.*, reported in journals, books, magazines, reports dissertations, thesis, *etc.*, or available at websites and have not included them in this thesis and have not cited as my own work.

Date: 31/12/2022

Place: Varanasi

*Vishwa Pratap Singh*  
(Vishwa Pratap Singh)

## CERTIFICATE BY THE SUPERVISOR

This is to certify that the above statement made by the candidate is correct to the best of my knowledge.

*Aksingh*  
(Dr. Akhilesh Kumar Singh)  
Supervisor  
Associate Professor  
School of Materials Science &  
Technology  
IIT (BHU), Varanasi

Associate Professor/सह-आचार्य  
School of Materials Science & Technology/पदार्थ विज्ञान एवं प्रौद्योगिकी स्कूल  
Indian Institute of Technology/भारतीय प्रौद्योगिकी संस्थान  
(Banaras Hindu University), Varanasi/काशी हिन्दू विश्वविद्यालय, वाराणसी

*31/12/22*  
Coordinator  
School of Materials Science &  
Technology  
IIT (BHU), Varanasi

Coordinator/समन्वयक  
School of Materials Science & Technology/पदार्थ विज्ञान एवं प्रौद्योगिकी स्कूल  
Indian Institute of Technology/भारतीय प्रौद्योगिकी संस्थान  
(Banaras Hindu University), Varanasi/काशी हिन्दू विश्वविद्यालय, वाराणसी





## COPYRIGHT TRANSFER CERTIFICATE

**Title of the Thesis:** “Semiconducting Nanoparticles/PVDF Nanocomposites with High Dielectric Strength for Capacitive Energy Storage”

**Candidate's Name:** Vishwa Pratap Singh

### Copyright Transfer

The undersigned hereby assigns to the Indian Institute of Technology (Banaras Hindu University), Varanasi all rights under copyright that may exist in and for the above thesis submitted for the award of the **Ph.D. degree**.

Date: 31/12/2022

Place: Varanasi

Vishwa Pratap Singh

(Vishwa Pratap Singh)

**Note:** However, the author may reproduce or authorize others to reproduce materials extracted verbatim from the thesis or derivative of the thesis for author's personal use provided that the source and the Institute's copyright notice are indicated.



## ACKNOWLEDGMENTS

---

Fore mostly, I would like to express my deep sense of gratitude to my supervisor **Dr. Akhilesh Kumar Singh**, Associate Professor, School of Materials Science & Technology, IIT(B.H.U.), Varanasi for his constant guidance and kind encouragement during PhD journey. I owe my entire work to him for his selfless support not only in academic but also his emotional support that he gave me during the difficult times. I have learned lots of things from him, such as how to think about things and most importantly to focus on the quality of work and not on the quantity. He is a pure cultivator of cutting-edge science and technology. I would like to thank him for everything and particularly for being my supervisor. I sincerely acknowledge his support during all sorts of hurdles in the execution of my thesis work as well as the personal difficulties. Further, I would like to thank **Dr. Akansha Dwivedi**, Assistant Professor, Ceramic Engineering IIT (BHU) for her support and guidance during my starting phase of the Ph.D. and continuous support.

I would also like to thank the faculty members of the School, Prof. Dhananjay Pandey, Prof. Rajiv Prakash, Prof. Pralay Maiti, Dr. Chandana Rath, Dr. Chandan Upadhyay, Dr. B. N. Pal, Dr. A. K. Mishra, Dr. S. K. Mishra, Dr. Sanjay Singh, Dr. Nikhil Kumar and Dr. Ravi Panwar for discussion during seminars and coursework studies. I am sincerely thankful to my RPEC members Dr. Ashutosh Dubey (Ceramic Engineering, IIT-BHU) and Dr. Sanjay Singh for their decent support, encouragement and guidance.

I would like to thank Dr. J. C Pandey, Assistant Professor, Department of Electrical Engineering, IIT-BHU, Varanasi and Dr. Tanmoy Maiti, Associate Professor, Material Science and Engineering, IIT Kanpur for providing descent support and encouragement.

I take this opportunity to express my heartfelt thanks to my seniors Dr. Prem Prakash (Ceramic Engineering, IIT BHU), Dr. Chandrabhal Singh, Dr. Dinesh Kumar for their technical support, emotional support and encouragement time to time whenever I required.

I would like to thank my labmates Dr. Vijyeta Pal, Mr. Ankit Dwivedi, Mr. Pragyan Prajapati, Mrs. Krishna Prajapati, Ms. Pooja Sonkar, Ms. Srishti Paliwal, Ms. Deep Mala, Mr. Prosun Mondal, Ms. Sadhana, Mr. Praveen and Mr. Jaikishan Pratap all belonging to SMST, IIT-BHU, Varanasi for providing their words of inspiration and encouragement.

I gratefully acknowledge CIF, IIT(BHU), Varanasi for providing various instrumental facilities.

I am also thankful to all, to whom I could not mention here who helped me directly or indirectly throughout the work. I am thankful to all non-teaching staff of the school for their cooperation at all levels.

I would like to thank my brotherly friend Mr. Satyendra Kumar Satyarthi for his support in everyday life. I am thankful to my best friend Mr. Abhay Kumar for his support in work life balance and encouragement in everyday life.

I express my indebtedness to my parents (Mr. Sodan Singh and Mrs. Dhan Devi) and grandparents for their love, affection, trust and support during every moment in my life. I would like to thank my maternal uncle and aunty for their support, trust and love. I would like to express my heartfelt appreciation to my life partner Ms. Sunita Payal for her emotional support, love, sacrifice and patience during my Ph. D time. I am especially indebted to my brothers and sisters whose love has contributed enormously to my strength and faith.

I am also thankful to all, to whom I could not mention here who helped me directly or indirectly throughout the work. I am thankful to all non-teaching staff of the School for their cooperation at all levels.

I take great pleasure in conveying my indebtedness to IIT-BHU, Varanasi and MHRD for granting me Institute Fellowship and providing all the facilities of the Departments/Schools/Centres to accomplish this research work.

I gratefully acknowledge the Indian Institute of Technology (Banaras Hindu University), Varanasi for providing me the necessary funding and fellowship to pursue research work.

Varanasi

(Vishwa Pratap Singh)

***“Nothing in life is to be feared, it is only to be understood. Now is the time to understand more, so that we may fear less.” Marie Curie***

***“Electric power is everywhere present in unlimited quantities and can drive the world’s machinery without the need of coal, oil, gas or any other of the common fuels.” Nikola Tesla***



# CONTENTS

Page No.

---

LIST OF FIGURES .....	xviii
LIST OF TABLES .....	xxvii
LIST OF SYMBOLS & ABBREVIATIONS.....	xxix
PREFACE.....	xxxii
<b>Chapter 1: Introduction and literature review .....</b>	<b>1</b>
<b>1.1 Dielectric and Ferroelectric materials.....</b>	<b>2</b>
1.1.1 Space charge (Interfacial) Polarization.....	4
1.1.2 Dipolar polarization .....	5
1.1.3 Ionic polarization .....	6
1.1.4 Electronic polarization .....	6
1.2 Electrical energy storage .....	10
1.3 PVDF(Homopolymer) and Its Ferroelectricity .....	11
1.4 Percolation threshold and interface phenomena.....	14
1.5 Breakdown Strength of dielectric materials .....	19
1.6 Enhancing the dielectric properties and energy density of PVDF.....	22
1.6.1 Modifying the defects.....	22
1.6.2 Blending and grafting the polymers .....	22
1.6.3 Using different filler to synthesize the PVDF based Nanocomposite .....	24
1.7 Application of PVDF based Nanocomposite films .....	40
1.8 Motivation of the thesis.....	41
1.9 Objective of the present work.....	42
<b>Chapter 2: Experimental (material and methods) and Characterization Techniques .....</b>	<b>44</b>
2.1 Introduction.....	44
2.2 Materials and Methods.....	45
2.2.1 Precursor .....	45
2.2.2 Synthesis of nanofiller.....	46
2.2.3 Synthesis of Polymer nanocomposite via solution cast method .....	49
2.3 Characterization techniques .....	50
2.3.1 Powder X-ray diffraction (XRD).....	50
2.3.2 Differential Scanning Calorimetry (DSC) .....	51
2.3.3 X-ray photoelectron spectroscopy (XPS).....	52
2.3.4 Photoluminescence spectroscopy .....	54
2.3.5 Scanning Electron Microscopy .....	56

2.3.6	Transmission Electron Microscopy .....	58
2.3.7	UV- Visible spectroscopy .....	60
2.3.8	Atomic Force Microscopy .....	61
2.3.9	Impedance Spectroscopy .....	62
2.3.10	Polarization-Electric field hysteresis loop characterization.....	64
2.3.11	AC Test set up .....	65
<b>Chapter 3: Enhancing the energy storage capacity of PVDF-based nanocomposite with the help of hydroxylated V<sub>2</sub>O<sub>5</sub> as filler .....</b>		<b>67</b>
3.1	Introduction.....	67
3.2	Synthesis of Hy-V <sub>2</sub> O <sub>5</sub> , PVDF/ Hy-V <sub>2</sub> O <sub>5</sub> nanocomposite films.....	68
3.3	Results and discussion .....	69
3.3.1	UV-Visible spectra and Tauc's plot of Hy-V <sub>2</sub> O <sub>5</sub> .....	69
3.3.2	X-Ray diffraction pattern analysis .....	70
3.3.3	Fourier-transform infrared spectroscopy (FTIR) Analysis and.....	71
3.3.4	X-ray photoelectron spectroscopy (XPS) analysis.....	73
3.3.5	Thermal Analysis using DSC-TGA .....	74
3.3.6	AFM micrograph analysis and roughness of film .....	76
3.3.7	Morphological analysis .....	79
3.3.8	Dielectric properties.....	80
3.3.9	Ferroelectric P-E loop analysis .....	82
3.3.10	Breakdown strength and energy density using Weibull analysis .....	83
3.3.11	Energy density and discharge efficiency from P-E loop.....	86
3.4	Theoretical analysis of percolation and interface thickness.....	89
3.5	Conclusions.....	90
<b>Chapter 4: Poly (vinylidene fluoride)/Nitrogen doped carbon dots nanocomposite film with improved storage properties for high energy density applications .....</b>		<b>92</b>
6.1	Introduction.....	92
6.2	Experimental .....	93
6.2.1	Synthesis of Nitrogen doped Carbon dots (N-CDs) .....	93
6.2.2	Synthesis of PVDF/N-CDs nanocomposite films .....	94
6.3	Result and Discussion .....	95
6.3.1	Characterization of N-CDs.....	95
6.3.2	Structural analysis PVDF/N-CDs with XRD, FTIR and DSC .....	97
6.3.3	XPS Analysis of the PVDF/N-CDs Films .....	102
6.3.4	AFM Micrographs analysis.....	104
6.3.5	Morphological analysis .....	106
6.3.6	Dielectric properties of PVDF/N-CDs nanocomposite films .....	108



6.3.7	Breakdown strength, P-E Hysteresis Loop and energy storage density .....	113
6.4	Theoretical analysis of percolation and interface thickness.....	120
6.5	Conclusions.....	121
<b>Chapter 5: Poly (vinylidene fluoride)/ hydrated antimony pentoxide (HAP) nanocomposite films for the application in high energy density storage supercapacitors .....</b>		<b>122</b>
5.1	Introduction.....	122
5.2	Experimental .....	123
5.2.1	Synthesis of Hydrated antimony pentoxide (HAP) .....	123
5.2.2	Synthesis of PVDF/HAP nanocomposite films .....	123
5.3	Results and Discussion.....	124
5.3.1	Characterization of filler Hydrated Antimony Pentoxide (HAP).....	124
5.3.2	Structural analysis of PVDF/HAP nanocomposite films .....	126
5.3.3	X-ray photoelectron spectroscopy (XPS) analysis.....	129
5.3.4	Morphological analysis of PVDF/HAP nanocomposite films.....	131
5.3.5	Dielectric and ferroelectric properties of PVDF/ HAP nanocomposite films .....	132
5.3.6	Breakdown strength, Energy density and Energy discharge efficiency of PVDF/HAP nanocomposite films .....	137
5.4	Conclusion .....	139
<b>Chapter 6: H<sub>2</sub>O<sub>2</sub> Hydroxylated rare earth ferrites (LaFeO<sub>3</sub> and GdFeO<sub>3</sub>) Nanofillers in Poly (Vinylidene Fluoride) based Nanocomposite Films .....</b>		<b>141</b>
8.1	Introduction.....	141
8.2	Experimental .....	142
8.2.1	GdFeO <sub>3</sub> , LaFeO <sub>3</sub> Nanoparticles Synthesis and Hydroxylation.....	142
8.2.2	Synthesis of Nanocomposite Film .....	142
8.3	Results and discussion .....	143
8.3.1	Structural Analysis .....	144
8.3.2	Morphological Analysis .....	147
8.3.3	Dielectric and Ferroelectric Properties .....	149
8.4	Conclusions.....	159
<b>Chapter 7: Summery and suggestions for future.....</b>		<b>161</b>
9.1	Conclusion .....	161
9.2	Suggestion for the future work.....	164
<b>Reference .....</b>		<b>166</b>
<b>List of Publications .....</b>		<b>184</b>
<b>List of Indian Patents.....</b>		<b>184</b>
<b>List of Conferences/Workshops/Seminars/Symposiums Attended .....</b>		<b>185</b>

## LIST OF FIGURES

Figure No.	Captions	Page No.
<b>Chapter 1</b>	<b>Introduction and literature review</b>	<b>1</b>
Figure 1.1	Categorization of the storage device according to energy and power.	3
Figure 1.2	Schematic diagram of space charge polarization in a capacitor.	5
Figure 1.3	Schematic diagram of the aligned dipole and non-aligned dipoles as the field application.	6
Figure 1.4	Schematic diagram of Ionic polarization at the applied field.	7
Figure 1.5	Showing the shifting of the charge on the application of the field.	8
Figure 1.6	Types of polarization varying with time and frequency.	9
Figure 1.7	Schematic diagram showing the shifting of the cation of the perovskite structure below the curie temperature.	10
Figure 1.8	Different type of materials under the Polarization and electric field characterization.	10
Figure 1.9	(a) Showing the Energy stored and energy lost.	12
Figure 1.10	(a) PVDF with different phase and (b) Process of the transformation of the phases of the PVDF.	13
Figure 1.11	Dominating phases of PVDF with their characteristics	13
Figure 1.12	(a) XRD, (b)FTIR and (c) DSC plots of the different phases of the PVDF.	14
Figure 1.13	Schematic diagram showing the percolation process.	15
Figure 1.14	Schematic diagram of the interface and dual layers.	16
Figure 1.15	Diagram showing the interface and inter-filler distance with dielectric constant variation	19

Figure 1.16	Showing the tradeoff between filler content in PVDF matrix with Debye length and inter-filler distance.	20
Figure 1.17	plot for the Weibull distribution.	21
Figure 1.18	Classification of the PVDF based Nanocomposites	25
Figure 1.19	(a) PE loop, (b) Dielectric constant, (c) Polarization variation, (d) Loss of the BaTiO <sub>3</sub> /PVDF with the size of the filler particles.	26
Figure 1.20	(a) Dielectric constant, (b) Loss, (c) PE loop, (d) Breakdown, of the PVP modified ST NP/PVDF and ST NP/PVDF with the size of the filler particles.	28
Figure 1.21	(a) PE loop, (b) Dielectric constant, (c) Polarization variation, (d) Loss of the BaTiO <sub>3</sub> /PVDF with the size of the filler particles.	29
Figure 1.22	(a) Breakdown Strength, (b) PE Loop, (c) Discharged Energy density, (d) discharged energy density of the TiO <sub>3</sub> @Sr TiO <sub>3</sub> @PDA/PVDF	31
Figure 1.23	(a) XRD of the NBT-NFs and PVDF, (b) Weibull analysis, (c) PE Loop, (d) Discharged Energy density, (e) discharged energy density (f) Breakdown strength variation of the NBT-NF/PVDF	33
Figure 1.24	(a) XRD pattern, (b) FTIR analysis (c) Dielectric constant, (d) PE loop (e) Discharged Energy density of the BiFeO <sub>3</sub> /PVDF	36
Figure 1.25	Dielectric constant of The TiC/PVDF (Inset) dielectric loss of the TiC/PVDF.	37
Figure 1.26	(a) Dielectric constant of the CCTO (solid solution)/PVDF, (b) Dielectric constant of the CCTO (Oxalate precursor)/PVDF and (c) Dielectric loss of the CCTO(Oxalate precursor)/PVDF, (d) Theoretical model fitting	38
Figure 1.27	(a) Dielectric constant, (b) dielectric loss of PVDF and CFO reinforced PVDF. (c) Dielectric constant and (d) dielectric loss of 20% CFO-1% GQD reinforced in PVDF composite with	39

	frequency. (e) Dielectric constant and (f) dielectric loss of GQD reinforced in PVDF composites	
Figure 1.28	(a) Dielectric Constant, (b) Dielectric loss, (c) P-E loop, (d) Energy density of PVDF and Nanocomposite films.	41
Figure 1.29	Application of the PVDF based Nanocomposite.	42
<b>Chapter 2</b>	<b>Experimental and Characterization Techniques</b>	<b>38</b>
Figure 2.1	Schematic of the solvothermal process	41
Figure 2.2	Schematic diagram of the mechanism inside the high energy ball mill	42
Figure 2.3	Schematic diagram of the hydroxylation of nanoparticles	43
Figure 2.4	Solution cast method of the nanocomposite film	44
Figure 2.5	Bragg's law for X-Ray diffraction schematic and diagram of the instrument.	45
Figure 2.6	X-Ray diffraction of the PVDF and it's nanocomposite.	46
Figure 2.6	(a) DSC Graph and (a) Instrument.	47
Figure 2.7	(a) Schematic diagram of mechanism of XPS, (b) XPS Instrument, (c) XPS Survey of PVDF/HAP.	49
Figure 2.8	(a) Schematic of photoluminescence spectroscopy, (b) instrument diagram and (c) output data.	50
Figure 2.9	(a) Ray diagram for SEM with (b) image of the EVO - Scanning Electron	51
Figure 2.9	(a) Ray diagram for SEM with (b) image of the EVO - Scanning Electron	52
Figure 2.10	Schematic diagram of TEM	53
Figure 2.11	(a) Schematic diagram of HR-TEM, (b) HR-TEM image of N-CDs.	54
Figure 2.12	(a) Schematic diagram of UV-Visible spectroscopy, (b) PL instrument and (c) data plot of UV-Vis.	55

Figure 2.12	(a) Schematic diagram of AFM, (b) Instruments and (c) 3D micrograph of AFM.	56
Figure 2.13	(a) Basic circuit diagram of Impedance spectroscopy, (b) Keysight instrument image and (c) Dielectric constant and temperature plot of the sample.	58
Figure 2.14	(a) Schematic Sawyer-Tower circuit for measurement of ferroelectric polarization, (b) The Radiant PE loop analyzer	59
Figure 2.15	(a) Image of Instrument AC Test set up, (b) Punctured sample after breakdown	61
<b>Chapter 3</b>	<b>Enhancing the energy storage capacity of PVDF-based nanocomposite with the help of hydroxylated V<sub>2</sub>O<sub>5</sub> as filler.</b>	<b>63</b>
Figure 3.1	The scheme of preparation of thick film of PVDF and PVDF/Hy-V <sub>2</sub> O <sub>5</sub> composites.	65
Figure 3.2	(a) UV-Vis spectra, band gap for (b) direct forbidden and (c) indirect allowed transition, using Tauc's plot for Hydroxylated V <sub>2</sub> O <sub>5</sub> .	66
Figure 3.3	XRD patterns of neat PVDF film and PVDF/Hy- V <sub>2</sub> O <sub>5</sub> nanocomposites thick films.	67
Figure 3.4	FTIR Spectra of (a) Hy- V <sub>2</sub> O <sub>5</sub> , (b) Pure PVDF and its nanocomposites with different filler volume percentage.	69
Figure 3.5	(a) XPS survey of PVDF, PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%), (b) V2p3/2 and V2p1/2, (c) F1s of PVDF, PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%), (d) C1s component of XPS spectra of PVDF, PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%).	70
Figure 3.6	(a) DSC of pure PVDF and all compositions of PVDF/Hy-V <sub>2</sub> O <sub>5</sub> (b) TGA thermograph of PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%).	72
Figure 3.7	(a) AFM micrograph (10x10μm) of Pure PVDF, (b) 3D AFM micrographs (10x10μm) of Pure PVDF, (c) AFM micrograph (10x10μm) of PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%) and (d) 3D AFM micrographs (10x10μm) of PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%).	74

Figure 3.	Roughness profile of (a) pure PVDF, (b) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%). Hann Windowing of AFM micrograph for (c) pure PVDF and (d) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%). (e) Isotropic 2D PSD Plot of PVDF and PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%).	74
Figure 3.8	SEM micro-topographies of (a) Hy-V <sub>2</sub> O <sub>5</sub> nanoparticles, (b) Histogram of the particle sizes of Hy-V <sub>2</sub> O <sub>5</sub> (c) pure PVDF, (d) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (1%), (e) PVDF/Hy-V <sub>2</sub> O <sub>5</sub> (3%), (f) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%), (g) Cross section of the nanocomposite film (PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%)), (h) Zoomed area of cross section of nanocomposite film.	74
Figure 3.9	SEM micro-topographies of (a) Hy- V <sub>2</sub> O <sub>5</sub> nanoparticles, (b) Histogram of the particle sizes of Hy- V <sub>2</sub> O <sub>5</sub> (c) pure PVDF, (d) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (1%), (e) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (3%), (f) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%), (g) Cross section of the nanocomposite film (PVDF/Hy- V <sub>2</sub> O <sub>5</sub> (5%)), (h) Zoomed area of cross section of nanocomposite film.	76
Figure 3.10	Dependence of dielectric constant and dielectric loss on frequency (a), (b); and temperature (c), (d) for pure PVDF and PVDF/Hy-V <sub>2</sub> O <sub>5</sub> nanocomposite films with different compositions.	78
Figure 3.11	Schematic diagram of dipoles under applied field for (a) pure PVDF film, (b) PVDF/Hy- V <sub>2</sub> O <sub>5</sub> film and (c) Ferroelectric P-E loops of PVDF and PVDF/Hy- V <sub>2</sub> O <sub>5</sub> nanocomposite films with different compositions at 1000kV/cm, 10Hz frequency	79
Figure 3.12	(a) Plot of Weibull distribution function parameters and (b) Energy density and Breakdown strength (Eb) of PVDF and PVDF/Hy-V <sub>2</sub> O <sub>5</sub> films with different compositions.	81
Figure 3.13	(a) Discharged energy density (Ud) (b) Schematic diagram for calculation of Energy storage efficiency.	82
Figure 3.14	(a) Schematic and 2D simulation of Nanocomposite, (b) Electric displacement field, (c) Electric field, (d) Energy density and (e) Space charge density.	84
Figure 3.14	(a) Schematic and 2D simulation of Nanocomposite, (b) Electric displacement field, (c) Electric field, (d) Energy density and (e) Space charge density.	85

<b>Chapter 4</b>	<b>Poly (vinylidene fluoride)/Nitrogen doped carbon dots nanocomposite film with improved storage properties for high energy density applications</b>	<b>87</b>
Figure 4.1	(a) Schematic diagram for synthesis of Nitrogen doped carbon dots.	89
Figure 4.1	Schematic diagram for synthesis of PVDF/N-CDs nanocomposite films.	90
Figure 4.2	(a) HR-TEM images of N-CDs, (b) Showing the particle distribution of N-CDs, (c) XRD Pattern and (d) FTIR spectrum.	91
Figure 4.3	(a) UV-Vis spectrum, PL Spectra of N-CDs excited at a wavelength of 375nm, (b) Tauc plot ( $(\alpha h\nu)^2$ vs $h\nu$ ).	92
Figure 4.4	(a) XRD, (b) FTIR, patterns of the of pure PVDF and PNC Nanocomposite	94
Figure 4.5	DSC Analysis of pure PVDF and Its nanocomposite films	96
Figure 4. 6	Schematic diagram of interaction between the PVDF matrix and loaded N-CDs filler.	97
Figure 4.7	(a) XPS Survey of PVDF and PNC, (b) N1s of PNC (1%), (c) F1s of the PVDF and PNC (1%) and (d) C1s of the PVDF and PNC.	98
Figure 4.8	Roughness profile of (a) pure PVDF, (b) PNC (1%), Isotropic 2D PSD Plot and Hann Windowing of AFM micrograph of (c) pure PVDF and PNC (1%), Surface image AFM of (d) PVDF and (e) PNC (1%).	100
Figure 4.9	FE-SEM micrographs of (a)PVDF/N-CDs (0.3%), (b) PVDF/N-CDs (0.3%), (c) PVDF/N-CDs (0.5%), (d) PVDF/N-CDs (1%), (e)Element mapping showing the presence of N-CDs	101
Figure 4.10	(a) Dielectric constant vs temperature, (b) loss vs temperature, (c) dielectric constant vs frequency, (d) loss vs frequency of nanocomposite films.	102

Figure 4.11	Temperature dependence of dielectric constant for (a) PVDF, (b) PNC (0.3%), (c) PNC (0.5%), (d) PNC (1.0%) films measured at various frequencies.	104
Figure 4.12	Temperature dependence of dielectric loss for (e) PVDF, (f) PNC (0.3%), (g) PNC (0.5%) and (h) PNC (1.0%) films measured at various frequencies.	105
Figure 4.13	AC conductivity for the nanocomposite films with varying (a) Temperature, (b) frequency.	106
Figure 4.14	(a) Electrical breakdown strength using Weibull analysis, (b) Sample image after breakdown showing puncture.	107
Figure 4.15	(a) P-E loop at 25Hz and (b) Discharge energy density and discharge energy efficiency for pure PVDF and nanocomposite films.	108
Figure 4.16	(a) Schematic diagram of dielectric constant measurement of N-CDs, (b) 2D Schematic of PVDF/N-CDs film, (c) Current density norm, (d) Polarization and (e) Electric field.	111
Figure 4.16	Hysteresis loop of PVDF/N-CDs (2wt%) at 10Hz.	113
<b>Chapter 5</b>	<b>Poly (vinylidene fluoride)/ hydrated antimony pentoxide (HAP) nanocomposite films for the application in high energy density storage supercapacitors</b>	<b>114</b>
Figure 5.1	Schematic diagram of synthesis process of PVDF/HAP nanocomposite.	116
Figure 5.2	(a) X-Ray diffraction pattern, (b) FTIR spectra pattern (C) UV-Vis and Tauc's plot (inset), (d) HR-SEM image and histogram(inset), of HAP.	117
Figure 5.3	(a) X-Ray diffraction pattern, (b) FTIR Spectra pure, PVDF and PVDF/HAP nanocomposite films	119
Figure 5.4.	DSC analysis of pure PVDF and PVDF/HAP nanocomposite films.	120
Figure 5.5	(a) XPS survey of the PVDH/HAP (8%), Zooming out the peak of (b) Sb, (c) F1s (d) C1s.	121



Figure 5.6	FESEM image of (a) pure PVDF Film, (b) PVDF/HAP (2%), (c) PVDF/ HAP (5%), (d) PVDF/ HAP (8%), (e) PVDF/ HAP (11%) and (f) Elemental mapping images of PVDF/ HAP (8%) with elements.	123
Figure 5.7	(a) Dielectric constant vs temperature, (b) Dielectric loss vs temperature, (c) Dielectric constant vs frequency and (d) Dielectric loss vs frequency, of all compositions.	125
Figure 5.8	The AC conductivity of the pure PVDF and nanocomposite films.	126
Figure 5.9	P-E hysteresis loop of all compositions	127
Figure 5.10.	Weibull distribution of all composition.	129
Figure 5.12	Discharged energy density and discharge energy efficiency of PVDF, PVDF/HAP nanocomposites as function of applied field at 1400kV/cm.	130
<b>Chapter 6</b>	<b>H<sub>2</sub>O<sub>2</sub> Hydroxylated rare earth ferrites (LaFeO<sub>3</sub> and GdFeO<sub>3</sub>) Nanofillers in Poly (Vinylidene Fluoride) based Nanocomposite Films</b>	<b>131</b>
Figure 6.1	Synthesis of PVDF/Hy-GdFO and PVDF/Hy-LFO nanocomposite films.	135
Figure 6.2	Schematic representation of PVDF-Filler bonding with the help of -OH.	136
Figure 6.3	XRD patterns of PVDF, GdFeO <sub>3</sub> (GdFO), PVDF/Hy-GdFO, LaFeO <sub>3</sub> (LFO) and PVDF/Hy-LFO.	137
Figure 6.4	The FTIR spectra of (a) hydroxylated LaFeO <sub>3</sub> (Hy-LFO), hydroxylated GdFeO <sub>3</sub> (Hy-GdFO nanoparticles, and (b) PVDF and PVDF/Hy-LFO, PVDF/Hy-GdFO nanocomposite.	138
Figure 6.5	DSC plot for PVDF and PVDF/Hy-LFO, PVDF/Hy-GdFO nanocomposite films.	139

Figure 6.6	FESEM micrographs of (a) LaFeO <sub>3</sub> with histogram(inset), (b) GdFeO <sub>3</sub> with histogram (inset), (c) pure PVDF, (d) PVDF/Hy-GdFO and (e) PVDF/Hy-LFO Nanocomposite film.	140
Figure 6.7	Temperature-dependent (a) dielectric constant, (b) dielectric loss; Frequency-dependent (c) dielectric constant and (d) dielectric loss; for pure PVDF and PVDF/Hy-LFO, PVDF/Hy-GdFO nanocomposite films measured at 1 kHz.	142
Figure 6.8	Comparison of dielectric constant and dielectric loss at 30°C (black columns) and 100°C (red columns) for pure PVDF; PVDF/Hy-GdFO and PVDF/Hy-LFO nanocomposite films.	143
Figure 6.9	Temperature dependence of dielectric constant and loss for PVDF, PVDF/Hy-GdFO, PVDF/Hy-LFO films measured at various frequencies.	144
Figure 6.10	Schematic diagram illustrating the formation of micro-capacitors in the nanocomposite due to loading of the filler.	145
Figure 6.11	(a) Dielectric constant and loss (inset) of the ferrite fillers, (b) Comparison of theoretical models and experimental data.	146
Figure 6.12	(a) AC conductivity vs temperature measured at 1kHz and (b) AC conductivity vs frequency at room temperature, for PVDF and nanocomposite films.	147
Figure 6.13	(a) P-E hysteresis loop of PVDF, PVDF/Hy-LFO and PVDF/Hy-GdFO nanocomposite films and (b) Energy density and energy discharge efficiency.	149
Figure 6.14	(a) Weibull Analysis of breakdown strength and (b) Comparison of breakdown strength and shape parameter ( $\beta$ ) for PVDF and ferrite nanocomposite films.	151

## LIST OF TABLES

Figure No.	Captions	Page No.
<b>Chapter 1</b>	<b>Introduction and literature review</b>	<b>1</b>
Table 2.1	The properties of the PVDF matrix and the fillers to be used.	39
<b>Chapter 2</b>	<b>Experimental and Characterization Techniques</b>	<b>38</b>
Table 3.1	Comparison of the performance of earlier reported systems with our nanocomposite.	83
<b>Chapter 4</b>	<b>Poly (vinylidene fluoride)/Nitrogen doped carbon dots nanocomposite film with improved storage properties for high energy density applications</b>	<b>87</b>
Table 4.1	Relative Proportion of electroactive phase in the PVDF and the Nanocomposites Filled N-CDs Obtained from the FT-IR, XRD Measurements.	95
Table 4.2	Pr and Pmax of PVDF and PVDF/N-CDs nanocomposite films and Energy density comparison calculated from different equations.	109
Table 4.3	Comparison of the dielectric constant, discharge energy density and discharge efficiency at the given electric field for the different nanocomposite films.	111
<b>Chapter 5</b>	<b>Poly (vinylidene fluoride)/ hydrated antimony pentoxide (HAP) nanocomposite films for the application in high energy density storage supercapacitors.</b>	<b>114</b>
Table 5.1	The Pmax and Pr of the all nanocomposite and pure PVDF.	127
<b>Chapter 6</b>	<b>H<sub>2</sub>O<sub>2</sub> Hydroxylated rare earth ferrites (LaFeO<sub>3</sub> and GdFeO<sub>3</sub>) Nanofillers in Poly (Vinylidene Fluoride) based Nanocomposite Films.</b>	<b>131</b>
Table 6.1	Values of maximum polarization and remanent polarization for PVDF and nanocomposite films determined from P-E loops at 800kV/cm applied electric field at 20Hz.	148
	Table 6.2. Comparison of energy density and dielectric constant with previously reported work.	149



## LIST OF SYMBOLS & ABBREVIATIONS

$\eta$	Energy efficiency
$\alpha$	Polarizability
$h\nu$	Photon energy
$E_g$	Band gap
$\nu$	frequency
$h$	Plank constant
$k$	Boltzmann Constant
$K$	Kelvin
$E_a$	Activation Energy
$U$	Energy density
$\text{\AA}$	Angstrom
$\psi$	Electric potential barrier
Hz	Hertz
T	Temperature
$T_c$	Curie temperature
$\chi$	Susceptibility
$\sigma$	Conductivity
$L_d$	Debye length
$V_{oc}$	Open-circuit voltage
$\phi$	Filler volume fraction
$\tau$	Life time of non-equilibrium carriers
$\delta_i$	Interfiller distance
$E_i$	Applied electric field specific value
$\mu\text{m}$	Micrometer
$\epsilon$	Dielectric Permittivity
$\tau$	Dielectric Relaxation Time
$\rho$	Total charge per unit area in electrode
$P$	Ferroelectric polarization
$E_c$	Coercive field
$P_{max}$	Maximum polarization
$P_s$	Spontaneous polarization

Pr	Remnant polarization
$E_b$	Breakdown strength
XPS	X-ray spectroscopy
AFM	Atomic force microscopy
C.B.	Conduction band
V.B.	Valence band
DW	Domain wall
FESEM	Field emission scanning electron microscopy
HRTEM	High resolution transmission microscopy
N-CDs	Nitrogen doped carbon dots
FTIR	Fourier transform infrared
HAP	Hydrated antimony pentoxide
PNC	PVDF/N-CDs
XRD	X-Ray diffraction
XPS	X-ray photoelectron spectroscopy
PL	Photoluminescence spectroscopy
UV-Vis.	Ultra Violet visible spectroscopy
AFM	Atomic force microscopy
PVDF	Polyvinylidene difluoride
rGO	Reduced graphene oxide
GND	Graphene nanodots
PSD	Power spectral density



## PREFACE

---

Energy storage is now garnering a lot of attention in the scientific community as a result of the current energy crisis and the severe air pollution. There is a significant need for the research and development of novel, environment friendly kinds of energy systems as well as associated energy storage technologies. Dielectric capacitors have the potential to be used in a variety of applications, including transport vehicles, fixed energy resources, and portable electronic gadgets because of their high-power density, long life, and cyclic life <sup>1</sup>. However, when compared to conventional batteries, the energy density of dielectric capacitors is rather poor, which stymies any attempts to further enhance these types of storage devices <sup>1,2</sup>. The capacitors have their own important and essential domain of applicability in the energy storage technologies due to their fast charging and discharging phenomena that batteries lacks of.

The dielectric capacitors generally are made of the dielectric materials having good storage properties. Ceramic materials like  $\text{PbTiO}_3$ ,  $\text{BaTiO}_3$  (BT),  $\text{BaZr}_{1-x}\text{Ti}_x\text{O}_2$  (BZT),  $\text{Ba}_{1-x}\text{Sr}_x\text{TiO}_3$  (BST) etc. have been used as the storage materials in the dielectric capacitors for long period of time and are still relevant in large amount of applications <sup>3-5</sup>. The ceramic dielectrics have high value of the dielectric constant, low dielectric loss and higher range of the temperature operation. Lead based dielectrics have breakdown strength within the range of 100 to 400  $\text{kV/cm}^2$  and energy density of 2 to 11  $\text{J/cm}^3$  <sup>2</sup>. However, Pb is carcinogen, so the use of Pb based material are restricted to employ and research on. BT based electroceramics could be the better replacement of lead-based dielectrics with the energy density of 1-5  $\text{J/cm}^3$  and breakdown strength of 145-450 $\text{kV/cm}$  <sup>6</sup>. Many other electroceramics has also been developed in last 20 years with comparable dielectric strength and energy density. However, the breakdown strength of the electroceramics is comparably lower that results in low energy density compare to the polymer nanocomposites. There are various polymers which shows very good dielectric properties. Polymers have moderate dielectric constant, high energy density



and large breakdown strength. The value of the dielectric constant of dielectric polymers is low as compare to dielectric ceramics. Polymer like PVDF, BOPP and PMMA have dielectric constant value of  $\sim 9$ ,  $\sim 2.3$  and  $4.9$  <sup>6</sup>. To achieve the desired properties for the storage applications, the polymers can be modified by synthesizing the nanocomposite. the polymer can be used as a matrix in nanocomposites. PVDF is very good dielectric polymer which is extensively being used by the researcher to get the better dielectric and storage properties. The synthesized polymer nanocomposites have demonstrated promising results. The dielectric ceramics with high dielectric constant have been used to get better properties of the polymer nanocomposites. These dielectric materials are being used as fillers in the polymer matrix as the required amount. BaTiO<sub>3</sub> based, lead based and SrTiO<sub>3</sub> based dielectric filler have been used as reinforcement in the PVDF matrix <sup>7,8</sup>. The results of these reinforcement in PVDF matrix have enhanced the dielectric constant and polarization. Enhancement in the polarization also enhanced the energy density of the polymer nanocomposite. The reinforcement of the dielectric ceramics in the PVDF have no limit, they can be reinforced to more than 50 vol% in PVDF to achieve desired energy density and dielectric properties. Reinforcement of the 60 vol% BaTiO<sub>3</sub> in PVDF matrix enhanced the dielectric constant from  $\sim 9$  to  $\sim 125$  with the modification of the surface of the surface of filler with PVP <sup>6</sup>. The latest research shows that the energy density of the PVDF/BaTiO<sub>3</sub> is  $8 \text{ J/cm}^3$  for 3vol% but as the volume % is increased the breakdown strength decreases abruptly, for 3vol%, breakdown strength is 78% of the PVDF and 36% for the 15vol% reinforcement of the filler in the PVDF matrix <sup>9</sup>. The same case is with the other electroceramics based dielectric fillers reinforced in the PVDF matrix. This trade-off between the dielectric properties and breakdown strength leads to think beyond the dielectric ceramic-based fillers.

The semiconducting/conducting nanoparticles are being used as nanofillers in the PVDF matrix. The low amount of the conducting/semiconducting filler can be used to enhance the

dielectric and storage properties as required as compare to the dielectric ceramic fillers. 1 vol% loading of the  $\text{TiO}_x$  in PVDF matrix leads to  $7.43 \text{ J/cm}^3$  with not substantial decrement in the breakdown strength as compare to PVDF<sup>10</sup>. To a particular vol% of such nanofiller, the energy density and breakdown strength are in favourable state but large amount leads to percolation in the nanocomposite. After percolation threshold, the nanocomposite becomes or behaves as partial conducting giving rise to enormous amount of the conducting paths in the films<sup>11</sup>. This problem can be solved by making better nanocomposite films using the modifying or refluxing agents to modify the nanoparticles surface. These refluxing have functional groups which helps the polymer chain to comfortably getting attached to the filler molecules<sup>12</sup>. Various types of the refluxing agents have been used to modify the nanoparticles.  $\text{H}_2\text{O}_2$ , PVP,  $\text{NH}_2$ - , PDOPA are potentially used in the previous researches resulting in positive response<sup>2,12</sup>.

In our present work, we have taken the PVDF as matrix for the nanocomposite films applicable in the high energy storage devices. PVDF have four phases with electroactive phases ( $\beta$ ,  $\gamma$ ) and  $\delta$ ,  $\alpha$ -phase as non-electroactive phase. The phases of the PVDF can be transformed from non-electroactive to electroactive by processing it or making nanocomposite with the suitable filler. The functional group present in hydroxylated filler helps PVDF to have all trans conformation. We have used the semiconducting nanomaterials to enhance the storage and dielectric properties of nanocomposite films. The modification of the nanoparticles is done with the help of hydroxylation of these with  $\text{H}_2\text{O}_2$ . The hydroxylated  $\text{V}_2\text{O}_5$  (Hy- $\text{V}_2\text{O}_5$ ), Hydrated antimony pentoxide (HAP), Hydroxylated  $\text{LaFeO}_3$ , Hydroxylated  $\text{GdFeO}_3$  and N-CDs.

### **1. PVDF reinforced with Hydroxylated $\text{V}_2\text{O}_5$ for the enhancement of energy storage properties**

We have synthesized poly (vinylidene difluoride) (PVDF)/Hydroxylated  $\text{V}_2\text{O}_5$  (Hy- $\text{V}_2\text{O}_5$ ) ferroelectric polymer nanocomposite self-standing film, with an average thickness of

0.07±0.005 mm. V<sub>2</sub>O<sub>5</sub> is actually a semiconducting material with some ferroelectric properties. So, it has been a good selection to reinforce in the PVDF matrix after hydroxylation. The phase identification, surface analysis and structural analysis was done using Differential Scanning Calorimetry (DSC), X-ray Photoelectron Spectroscopy (XPS) analysis, X-Ray Diffraction (XRD) respectively. Atomic force microscopy (AFM) micrographs' analysis reveals lower surface roughness of the nanocomposite films and confirms that the film is suitable for energy storage rather than charge transport with the help of isotropic power spectral density (PSD) profile. The loading of low amount of Hy-V<sub>2</sub>O<sub>5</sub> filler in PVDF significantly enhances the ferroelectric polarization, making it highly suitable for the high energy storage applications. The enhancement in the dielectric constant (from ~9 to 29.86) and polarization (P<sub>max</sub> for PVDF = 0.86 μC/cm<sup>2</sup> to P<sub>max</sub> for PVDF/Hy-V<sub>2</sub>O<sub>5</sub> = 2.7 μC/cm<sup>2</sup> at the 1000 kV/cm field) is obtained. The energy density for nanocomposite increased to 220% of pure PVDF. Due to the low amount of filler, there is no substantial reduction in the dielectric breakdown strength of the nanocomposite, which is maintained at 1766.93 kV/cm.

## **2. Loading of N-Carbon Dots in PVDF as Two Phase-Based Nanocomposite Film to Enhance Dielectric and Storage Properties for High Energy Density Supercapacitor**

The facile synthesis of Nitrogen-doped carbon dots (N-CDs) and the Poly (vinylidene fluoride)/N-CDs based self-standing nanocomposite film. The N-CDs are semiconducting in nature and introduce interfacial interaction with the PVDF matrix. The loading of N-CDs nanofiller in the PVDF matrix accelerates the formation of more electroactive phases and increases the crystallinity of the nanocomposite films, which has been confirmed with the help of XRD, FTIR, and DSC analysis. The dielectric and ferroelectric properties of nanocomposite films are improved with the addition of N-CDs in the polymer matrix having a dielectric constant ( $\epsilon_r$ ) of 19.59 at room temperature as compared to neat PVDF having  $\epsilon_r = \sim 9$  at 1kHz. At 1wt% of N-CDs loading in the PVDF matrix, the maximum polarization for nanocomposite

is  $4.164 \mu\text{C}/\text{cm}^2$  as compared to pure PVDF ( $1.79 \mu\text{C}/\text{cm}^2$ ) with a comparatively minor increment in loss. The overall positive is that the enhancement in energy density to ( $U_d$ ) ( $2.38\text{J}/\text{cm}^3$ ) for Nanocomposite film for 1% filler.

### **3. Poly (vinylidene fluoride)/ hydrated antimony pentoxide (HAP) based nanocomposite film with improved dielectric and storage properties**

We have synthesized the nanocomposite film with polymer as matrix and hydrated antimony pentoxide (HAP) as conducting filler. Thus, the hydroxylation of nano powder  $\text{Sb}_2\text{O}_3$  was done to enhance proton conductivity and as well as developing reactivity in  $\text{Sb}_2\text{O}_3$  to use as a conducting filler in PVDF matrix. The hydroxylated  $\text{Sb}_2\text{O}_3$  is actually hydrated antimony pentoxide (HAP) having  $\text{H}_3\text{O}^+$  and  $\text{H}^+$ . The proton conductivity of the HAP is confirmed with the help of XRD. The nanocomposite films (PVDF/HAP) were synthesized with the help of solution cast process. The phase identification of nanocomposite films was done with the help of XRD, FTIR and morphological analysis is done with FE-SEM. The measured dielectric constant of nanocomposite film is around 27.86, for 8% filler in comparison of pure PVDF with 9.56. The polarization of nanocomposite film is  $2.91 \mu\text{C}/\text{cm}^2$  with 8% filler loading while for 0% filler in PVDF polarization is around  $1.11 \mu\text{C}/\text{cm}^2$  at  $1400\text{kV}/\text{cm}$  field. Weibull analysis is done to calculate the breakdown strength. The energy density at an electric field  $1400\text{kV}/\text{cm}$  is  $1.59 \text{J}/\text{cm}^3$  for nanocomposite, for pure PVDF it is  $0.66 \text{J}/\text{cm}^3$ .

### **4. $\text{H}_2\text{O}_2$ Hydroxylated rare earth ferrites ( $\text{LaFeO}_3$ and $\text{GdFeO}_3$ ) Nanofillers in Poly (Vinylidene Fluoride) based Nanocomposite Film.**

we synthesized the  $\text{LaFeO}_3$  and  $\text{GdFeO}_3$  nanoparticles with the help solid state method. The  $\text{H}_2\text{O}_2$  Hydroxylated,  $\text{LaFeO}_3$  (Hy-LFO) and  $\text{GdFeO}_3$  (Hy-GdFO) nano-particles were used for the first time as filler in the PVDF to get nanocomposite films with improved dielectric and ferroelectric properties. The solution cast method has been used for the preparation of the

nanocomposite films. The H<sub>2</sub>O<sub>2</sub> Hydroxylation improved the interfacial interaction between the filler and the PVDF matrix. X-ray diffraction (XRD) and Fourier transform infrared spectroscopy (FTIR) spectra analyses confirmed the formation of polar phases ( $\beta$ ,  $\gamma$ -phases) of PVDF in dominance with non-polar phase ( $\alpha$ -phase) after nanocomposite formation. Differential Scanning Calorimetry (DSC) measurements reveal that the peak corresponding to the  $\alpha$ -phase of PVDF is fully diminished in the nanocomposite films. The increment in polar phase fraction in developed nanocomposite films results from the interfacial interaction due to nanofiller. The ferroelectric hysteresis loop recorded for the PVDF/Hy-LFO, PVDF/Hy-GdFO nanocomposite films; reveals relatively improved polarization as compared to pure PVDF.

We have got better response from the reinforcement of the N-CDs in PVDF followed by the HAP. Hy-V<sub>2</sub>O<sub>5</sub> and rare earth ferrites have also enhanced the storage properties.

These studies and findings are not only beneficial to study the enhancement of the PVDF nanocomposite films but also provide the evidence that the low amount of the semiconducting fillers can give better response with the low amount. The results provided in our research work can provide the direction to research further for better filler and nanocomposites. These results can also be used as the application in the devices for the energy storage purposes.

The thesis is organized into 7 chapters.

**Chapter 1:** This chapter start with introduction about the PVDF nanocomposite and its application in capacitive energy storage. Further gives exposé to the basic concepts related to the capacitors, dielectric materials expanding to the concepts like ferroelectricity, energy density and breakdown strength with understanding of the polymer nanocomposite. A concise review of the recent progress in the PVDF nanocomposite materials for the application in high energy storage is presented.

**Chapter 2:** This chapter describes the materials used in synthesis of the PVDF nanocomposite films. The synthesis process and methods have been discussed in detail. The solution cast process of the film making is described. A brief description of various characterizing techniques used in the research work has been presented.

**Chapter 3:** This chapter is dedicated to the PVDF Nanocomposite films reinforced with the Hy-V<sub>2</sub>O<sub>5</sub>. The response of the reinforcement has been discussed in details with the help of various characterization techniques. The energy storage properties of the nanocomposite film studied in detail with impedance analyzer and PE loop analyzer. Breakdown strength calculated with the help of the Weibull analysis.

The work presented in this chapter has been published in the ACS Applied Energy Material (Impact Factor = 6.95) (<https://doi.org/10.1021/acsaem.2c02425>)

**Chapter 4:** Chapter discussed the reinforced N-CDs in the PVDF matrix and shows very fascinating results in energy storage. N-CDs are semiconducting in nature, characterized by the UV and PL with the HRTEM and further loading in PVDF matrix to synthesize nanocomposite film, the characteristics of the films have been done with the help of various instruments. The parameters are calculated with the standard formulas to know the response.

**Chapter 5:** Synthesis of PVDF nanocomposite reinforced with the HAP as filler has been studied in detail in this chapter. The enhancement in the dielectric and energy storage parameters have been calculated after collecting data from the instruments. The phase and structure analyzed with the help of various characterization techniques.

**Chapter 6:** In this chapter, we have studied the energy storage properties of rare earth ferrite reinforced in the PVDF nanocomposite matrix. LaFeO<sub>3</sub> and GdFeO<sub>3</sub> are used as filler in PVDF and the reinforcement effect on the PVDF matrix studied with the help of characterization techniques. The enhancement in the dielectric and polarization properties is analyzed and

discussed in detail with time and frequency dependent data collected from the impedance spectroscopy analyzer and PE Loop analyzer.

The work from this chapter has been published in Springer Journal of Material Science: Material in Electronics (Impact Factor = 2.78) (<https://doi.org/10.1007/s10854-022-08836-z>)

**Chapter 7:** Summarizes the main findings of the present research work done and suggestions for the future investigations and studies.